Washable, durable and flame retardant conductive textiles based on reduced graphene oxide modification

DOI:

[10.1007/s10570-019-02884-1](https://doi.org/10.1007/s10570-019-02884-1)

Document Version

Accepted author manuscript

[Link to publication record in Manchester Research Explorer](#)

Citation for published version (APA):

Zhao, Y., Wang, J., Li, Z., Zhang, X., Tian, M., Zhang, X., Liu, X., Qu, L., & Zhu, S. (2019). Washable, durable and flame retardant conductive textiles based on reduced graphene oxide modification. *Cellulose*.
<https://doi.org/10.1007/s10570-019-02884-1>

Published in:

Cellulose

Citing this paper

Please note that where the full-text provided on Manchester Research Explorer is the Author Accepted Manuscript or Proof version this may differ from the final Published version. If citing, it is advised that you check and use the publisher's definitive version.

General rights

Copyright and moral rights for the publications made accessible in the Research Explorer are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

Takedown policy

If you believe that this document breaches copyright please refer to the University of Manchester's Takedown Procedures [<http://man.ac.uk/04Y6Bo>] or contact uml.scholarlycommunications@manchester.ac.uk providing relevant details, so we can investigate your claim.

Washable, Durable and Flame Retardant Conductive Textiles Based on Reduced Graphene Oxide Modification

Yintao Zhao,^{a,b,c} Jin Wang,^{a,b,c} Zengqing Li,^{a,b,c} Xiangwu Zhang,^e Mingwei Tian,^{a,b,c}
Xiansheng Zhang,^{a,b,c} Xuqing Liu,^{d*}, Lijun Qu,^{a,b,c*} Shifeng Zhu^{a,b,c*}

^a College of Textiles and Clothing, Qingdao University, Qingdao, Shandong, 266071, China

^b Research Center for Intelligent and Wearable Technology, Qingdao University, Qingdao,
Shandong, 266071, China

^c State Key Laboratory of Bio-Fibers and Eco-Textiles, Qingdao University, Qingdao,
Shandong, 266071, China

^d The University of Manchester, School of Materials, Manchester, M13 9PL, UK

^e Wilson College of Textiles, North Carolina State University, Raleigh, NC 27695, USA

Keywords Polyester/cotton fabric; Graphene oxide; Phosphate flame retardant;
Electrical surface resistivity; Flame retardancy

Abstract Graphene has been highlighted in a variety of wearable electronics and smart textiles applications due to its unique properties such as high conductivity, transparency, flexibility and other excellent mechanical performance. Although there have been extensive efforts for graphene based conductive fibers/yarns, there are remaining challenges in terms of the seamless integration between 2D flakes, and reduced charge transport in a lower carrier concentration. Unstable resistance probably arises from the creation of gaps in the conductive parts of the smart textile.

Also, regional temperatures can get too high, constituting a fire-safety hazard and endangering the wearer's safety. In this work, the synergistic effect of graphene and flame-retardant materials was investigated, and a conductive fabric was developed which is highly conductive and flame retardancy. Graphene has excellent electrical and thermal conductivity and acts synergistically with traditional flame-retardants on common fabrics. The electrical surface resistivity of hybrid material modified fabrics was as low as 0.54 kΩ/sq, so they could serve as safe and highly conductive conductor in a simple circuit and show excellent wash-ability. The limiting oxygen index of the fabric increased from 19 to 32 after modification in conjunction with the residue at 800 °C increased from 17.9% to 31%, which could be used as safe and highly conductive materials for smart textiles and wearable devices.

Introduction

Smart textiles have increased exponentially in recent years, being used in many applications such as health, sport, automotive, aerospace and military (Grancarić et al. 2018; Gu et al. 2010). To function as smart textiles, electrical conductivity is a fundamental essential (Zahid et al. 2017; Qing et al. 2019; Cataldi et al. 2017). Many studies have been carried out to fabricate conductive textiles according to these demands and demonstrated in various applications (Simorangkir et al. 2018; Atalay et al. 2018; Zhang and Shi 2019; Huang et al. 2016). Unfortunately, the risk of combustion of electrically conductive fabrics in case of unstable resistance was neglected. For functional textiles, such as fireman garments, various flame retardants have been used to improve the flame retardancy and thermal stability of textile materials such as cotton, polyester/cotton, silk and wool fabrics (Chen et al. 2019; Pan

et al. 2018; Gashti et al. 2013a; Gashti and Gashti. 2013; Gashti et al. 2012). However, the flame-retardant treatment of the wearable electronics and smart textiles appears rarely in the literature. The aim of the present work was to impart electrical conductivity and flame retardancy to polyester/cotton fabric which is the most widely used fabric material for apparel and technical applications.

Graphene oxide (GO) is a graphene derivative with many polar groups that can easily bind with fiber surfaces (Qu et al. 2019), and it is hydrophilic and can disperse in water readily (Saxena et al. 2011; Cai et al. 2017). Various reduction methods were developed to restore its excellent thermal conductivity, electrical conductivity, and mechanical performance (Gashti and Almasian (2013); Fathy et al. 2019; Nooralian et al. 2016; Voiry et al. 2016). In recent years, many kinds of conductive fabrics have been prepared using reduced graphene oxide (Ding et al. 2019). A cotton fabric with electrical conductivity was fabricated by the deposition of graphene oxide dispersion and hot press reduction, the sheet resistance of modified cotton fabric reduced to 0.9 k Ω /sq (Ren et al. 2017). Nylon-6 yarns, cotton yarns, polyester yarns, and nonwoven fabrics with conductivity were prepared successfully with the addition of graphene oxide and bovine serum albumin (Yun et al. 2013). Additionally, graphene oxide together with other substances has been employed to improve the flame retardancy of materials (Tian et al. 2016; Liu et al. 2019; Feng et al. 2019). The flame retardancy of polypropylene nanocomposites was improved using graphene/multi-walled carbon nanotubes (Huang et al. 2014). The intumescent flame retardant poly(butylene succinate) composites with good flame retardancy were prepared with the application

of graphene (Wang et al. 2011). Thermal stability and flame retardancy of epoxy resin were significantly improved with the addition of graphene nanosheets (Liu et al. 2014).

In this study, graphene oxide and phosphorus flame retardant were chosen to modify polyester/cotton fabric using the conventional dip-immersion method. The structure, electrical resistance, flammability and thermal property of the fabric have been investigated, and a universal, safe, highly conductive textile material was provided to be used in smart textiles and wearable devices.

Materials and Methods

Materials

Polyester/cotton fabric (PET/CO65/35, 238 g/m²) was purchased from Qingdao Xu Teng Textile Co., Ltd. Phosphate flame retardant (PFR) was provided by Qingdao Lianmei chemical industry. Aqueous solution of GO (5 g/L) was prepared using flake graphite powder according to modified Hummers' method (Zhao et al. 2018). Large flake graphite powder was kindly provided by Qingdao Huatai Tech Co., Ltd. Hydrochloric acid (37%), sulfuric acid (98%), and other reagents were purchased from Tianjin Chemical Reagent Co. Ltd. The reducing agent powder was provided by Ji'nan Tian Shuo Chemical Co., Ltd. The adhesive Goon was provided by Jiahong organic silicon technology Co., Ltd. The distilled water was used in the experiment.

Preparation of modified polyester/cotton fabric

The conventional dip-immersion method was used to modify polyester/cotton fabric. The original fabric (PET/CO), the fabric with reduced graphene oxide (PET/CO-rGO), and the fabric treated with flame retardant (PET/CO-PFR) were chosen as the control samples. The preparation route of the modified fabric (PET/CO-rGO-PFR) was

92 shown in Fig. 1. The fabric was firstly soaked in graphene oxide solution for 2 h to
 93 become yellowish-brown and the fabric was squeezed with a small rolling mill to dry
 94 at room temperature. Secondly, the fabric was reduced at the temperature of 90 °C for
 95 1.5 h and the color of the fabric changed to black, which was caused by the reduction
 96 of graphene oxide. This step could be repeated many times to obtain better electrical
 97 conductivity. Finally, the sample was dipped and pressed twice in phosphate flame
 98 retardant solution, and dried at 90 °C for 10 mins, 150 °C for 3 mins. To improve the
 99 durability of the modified fabric, the sample was treated in adhesive solution (Goon,
 100 10 wt%) for 30 mins and dried at 100°C for 15 mins.

101
 102 **Fig. 1** Preparation route of PET/CO-rGO-PFR fabric

103 Characterization and measurement

104 Raman (DXR2, Thermo Scientific, America) spectra were utilized to analyze the G
 105 and D peaks of graphene oxide and reduced graphene oxide on the modified fabric.
 106 Fourier transform infrared (FTIR) spectra of all samples were obtained by NICOLET
 107 iS5 (Thermo Scientific, America) within the wavelength 500-4000 cm⁻¹ (KBr disk).
 108 The microstructure of samples was measured by scanning electron microscope (SEM,

EVO18, ZEISS, Germany). Four-point probe technique (RTS-8, Probes Tech, China) was utilized to measure the electrical conductivity, the resistances of ten different positions were gauged to obtain the average value.

The limiting oxygen index (LOI) was tested according to ASTM D2863-08 standard, 10 specimens were prepared for each sample with the size of 5*15 cm. Burning behaviors of samples were measured by vertical flame test (VFT) based on GB/T5455-1997 with the size of 5*12 cm. The thermo gravimetric analysis (TGA, TG209F3, Tarsus, German) was ranged from 50 °C to 800 °C with the heating rate 10 °C/min.

Results and discussion

Raman spectroscopy and Fourier transform infrared spectroscopy

Raman spectra were utilized to analyze the peaks on PET/CO-GO and PET/CO-rGO.

As shown in Fig. 2a, G peak at 1590 cm^{-1} was higher than D peak at 1310 cm^{-1} in PET/CO-GO. But the phenomenon is quite different in Fig. 2b, D peak occupied the dominant position and the intensity of D peak was higher than G peak with the ratio of ID/IG was 1.23. It can be attributed to the diminishment of sp^2 in average size during reduction process. New graphitic domains established and their increase in number proved the well reduction of GO (Stankovich et al. 2007).

The characteristic peaks of rGO, PFR, PET/CO, PET/CO-rGO, PET/CO-PFR and PET/CO-rGO-PFR were listed in Fig. 2c-d. The peaks of PET/CO appeared at 1709 cm^{-1} , 1238 cm^{-1} , 1104 cm^{-1} , 1025 cm^{-1} were corresponding to stretching vibration of C=O, asymmetric stretching of aromatic ester, ring asymmetric stretching and stretching vibration of C-O respectively. The peaks between 3600 cm^{-1} and 3000 cm^{-1} represented the hydrogen bonded OH stretching (Carrillo et al. 2004; Alimohammadi et al. 2018; Palaskar et al. 2011). After the final modification, the new peaks appeared

at 1667 cm^{-1} , 1545 cm^{-1} , 1420 cm^{-1} , 1238 cm^{-1} , 1025 cm^{-1} , 827 cm^{-1} corresponding to the bond stretch of C=C, condensed aromatic ring O-H, carboxylic O-H, P-O-C aromatic stretching, C-OH stretching and P-CH₂ bond, respectively (Carrillo et al. 2004; Palaskar et al. 2011; Gaan and Sun 2007; Gashti et al. 2013a; Ren et al. 2007; Gashti et al. 2013b; Shin et al. 1997). It indicated that the flame retardant and rGO were coated on the surface of the fabrics successfully.

Fig. 2 Raman spectrum of (a) PET/CO-GO and (b) PET/CO-rGO, and FTIR spectra of (c) rGO and PFR, (d) PET/CO, PET/CO-rGO, PET/CO-PFR and PET/CO-rGO-PFR

SEM was used to investigate the micromorphology of samples and the images are illustrated in Fig. 3. The surface of PET/CO was smooth without any other substances seen from Fig. 3a1-a2. After modified by rGO, a thin film could be observed vaguely

147 on the surface of the fibers (Fig. 3b1-b2). Being treated by PFR, the surface of fibers
148 was covered with PFR as shown in Fig. 3c1-c2. When reduced graphene oxide and
149 PFR were both introduced to the fabric, the continuous and integrated film was
150 formed on the surface of the fibers showing the effective combination of PFR and
151 rGO (Fig. 3d1-d2).

Fig. 3 SEM images of (a1, a2) PET/CO, (b1,b2) PET/CO-rGO, (c1,c2) PET/CO-PFR, (d1,d2) PET/CO-rGO-PFR

Electrical surface resistivity

As we all know, polyester/cotton fabric was non-conductive. After once **modification**, PET/CO-rGO and PET/CO-rGO-PFR showed small electrical surface resistivity

2.104 k Ω /sq and 2.117 k Ω /sq respectively. With the increase of reduction times, the electrical surface resistivity decreased furtherly. After being reduced five times, the electrical surface resistivity of fabric reached 0.551 k Ω /sq and it increased to 0.559 k Ω /sq after adding PFR which indicated that the existence of PFR showed on negative effect on the electrical conductivity. To show the practical application, light bars and button batteries were connected by PET/CO-rGO-PFR on T-shirt (Fig. 4a), the connecting mode of circuit was exhibited in the left bottom of Fig. 4a. When the circuit was switched on, the light bar lightened up.

Fig. 4 (a) T-shirts with circuits containing PET/CO-rGO-PFR, and the little picture in (a) is a circuit connected by PET/CO-rGO-PFR (b) Correlation between electrical surface resistivity and washing cycles

To improve the washing fastness of PET/CO-rGO-PFR, the adhesive was used after reduction and the electrical surface resistivity changed a little to 0.546 k Ω /sq. The relationship between the electrical surface resistivity and washing cycles was illustrated in Fig. 4b indicating that PET/CO-rGO-PFR had good wash resistance with the existence of adhesive.

Flame retardant property

The images of different samples after Vertical flame test (VFT) were exhibited in Fig. 5a-d. The results showed that PET/CO-PFR and PET/CO-rGO-PFR extinguished themselves, while PET/CO and PET/CO-rGO kept burning after ignition. The

introduction of rGO decreased the damage length from 3.7 cm to 3.3 cm compared with PET/CO-PFR. LOI test was employed to investigate the flame-retardant property of different samples. LOI values of PET/CO, PET/CO-rGO, PET/CO-PFR and PET/CO-rGO-PFR were 19, 20.6, 31, 32, respectively, which indicated that rGO had a synergetic effect on the flame retardancy.

The samples were exerted in the circuit for a long time as shown in Fig. 5e-h. There were smoke and spark of the electrically conductive fabric PET/CO-rGO. After treated by PFR, the circuit operated safely under the same conditions to avoid the combustion.

Fig. 5 Images of the samples after VFT (a) PET/CO, (b) PET/CO-rGO, (c) PET/CO-PFR, (d) PET/CO-rGO-PFR, and under voltage connecting (e) PET/CO, (f) PET/CO-rGO, (g) PET/CO-PFR, (h) PET/CO-rGO-PFR

Thermal property

Thermal decomposing behaviors of four samples were evaluated by thermogravimetric analysis (TGA). TG and DTG curves were shown in Fig. 6a and Fig. 6b. Fig. 6c and Fig. 6d were bar graphs of key data in accordance with TG and DTG curves.

Observing from Fig. 6a and Fig. 6c, the initial decomposition temperature of

untreated PET/CO fabric was 274 °C while the temperatures of PET/CO-PFR and PET/CO-rGO-PFR were both 127 °C. The existence of PFR had great effect on the initial decomposition temperature and the addition of rGO did not change the result. The existence of rGO promoted the charring of the fabric and the residues of samples at 800°C were 17.9%, 30.7%, 31%, respectively.

As shown in Fig. 6b, there were two peaks in the DTG curves. The former corresponded to cotton while the latter to polyester (Rahimi et al. 2011). Fig. 6d gave the specific data about DTG curve, the former peaks of the sample treated by PFR and the sample treated by PFR/rGO appeared at 290 °C, which were lower than the original fabric at 355 °C. But the decomposition rate slowed down from 0.37 %/°C to 0.23 %/°C. As for the second peaks, it slowed down from 1.51 %/°C to 1.33 %/°C. It indicated that PFR lowered the weight loss rate and the addition of rGO promoted it furtherly. It can be interpreted as that phosphorus had a positive effect on flame retardancy of cellulose fibers including cotton and promoted the formation of carbon (El-Shafei et al. 2015). On the other hand, the reduced graphene oxide affected the flame retardancy of polyester for the char formation (Palaskar et al. 2011; Huang et al. 2012).

Fig. 6 (a) TGA and (b) DTG curves of PET/CO, PET/CO-PFR, PET/CO-rGO-PFR, the corresponding data of (c) DTG and (d) TG

Conclusions

In order to develop a non-ignitable electrically conductive fabrics, reduced graphene oxide and phosphate flame retardant were used to modify polyester/cotton fabric. There was cooperative effect between reduced graphene oxide and the flame retardant. Low electrical surface resistivity as 0.54 kΩ/sq was achieved, and the introduction of flame-retardant and adhesive had little effect on the surface resistivity. Also, the modified polyester/cotton fabric had good fastness to washing. The existence of rGO improved the flame retardancy compared with the fabric using PFR only. The value of LOI increased from 19 to 32 and the vertical flame test indicated that the damage length reduced to 3.3 cm during the ignition time, while the original fabric got ruined

entirely. TG and DTG curves showed that thermal stability of fabric improved significantly with a decrease in the maximum mass lose rate.

Acknowledgements The authors would like to acknowledge the financial assistance provided by National Key R&D Program of China (No 2017YFB0309000) and National Natural Science Foundation of China (No 51672141).

Conflicts of Interest

The authors declare no conflicts of interest.

References

Alimohammadi F, Gashti M P, Mozaffari A (2018) Polyvinylpyrrolidone/Carbon Nanotube/Cotton Functional Nanocomposite: Preparation and Characterization of Properties. *Fiber. Polym* 19: 1940-1947.

Atalay O, Atalay A, Gafford J, Walsh C (2018) A Highly sensitive capacitive-based soft pressure sensor based on a conductive fabric and a microporous dielectric layer. *Adv. Mater. Technol* 3:1700237-1700244.

Cai G, Xu Z, Yang M, Tang B, Wang X (2017) Functionalization of cotton fabrics through thermal reduction of graphene oxide. *Appl Surf Sci* 393: 441-448.

Cataldi P, Ceseracciu L, Athanassiou A, Bayer IS (2017) Healable cotton–graphene nanocomposite conductor for wearable electronics. *ACS Appl. Mater. Interfaces* 9:13825-13830.

Carrillo F, Colom X, Sunol JJ, Saurina J. (2004) Structural FTIR analysis and thermal characterisation of lyocell and viscose-type fibres. *Eur. Polym. J.* 40: 2229-2234.

Chen T, Hong J, Peng C, Chen G, Yuan C, Xu Y, Dai L (2019) Superhydrophobic and

251 flame-retardant cotton modified with DOPO and fluorine-silicon-containing
 252 crosslinked polymer. *Carbohydr. Polym* 208: 14-21.

253 Ding X, Lei S, Du C, Xie Z, Li J, Huang X (2019) Small-Sized CuS Nanoparticles/N,
 254 S Co-Doped rGO Composites as the Anode Materials for High-Performance
 255 Lithium-Ion Batteries. *Adv. Mater. Interfaces* 6:1900038.

256 El-Shafei A, ElShemy M, Abou-Okeil A (2015) Eco-friendly finishing agent for
 257 cotton fabrics to improve flame retardant and antibacterial properties. *Carbohydr.*
 258 *Polym* 118:83-90.

259 Fathy M, Moghny TA, Mousa MA (2019) Fast and Fully Scalable Synthesis of
 260 Graphene Oxide from Cellulose by Catalytic Acid Spray Method. *Arabian J. Sci.*
 261 *Eng* 44:305-313.

262 Feng Y, Li X, Zhao X, Ye Y, Zhou X, Liu H, Xie X (2019) Synergetic improvement in
 263 thermal conductivity and flame retardancy of epoxy/silver nanowires composites
 264 by incorporating “Branch-Like” flame-retardant functionalized graphene. *ACS*
 265 *Appl. Mater. Interfaces* 10:21628-21641.

266 Gaan S, Sun G (2007) Effect of phosphorus and nitrogen on flame retardant cellulose:
 267 a study of phosphorus compounds. *J. Anal. Appl. Pyrolysis* 78:371-377.

268 Gashti MP, Navid MY, Rahimi MH (2012) Coating of macroemulsion and
 269 microemulsion silicones on poly (ethylene terephthalate) fibers: Evaluation of
 270 the thermal properties and flammability. *J. Appl. Polym. Sci* 125:1430-1438.

271 Gashti MP, Navid MY, Rahimi MH (2013) Effects of coating of nano-and
 272 microemulsion silicones on thermal properties and flammability of polyethylene
 273 terephthalate textile. *Pigm. Resin Technol* 42:34-44.

274 Gashti MP, Gashti MP (2013) Effect of colloidal dispersion of clay on some properties

275 of wool fiber. J. Dispersion Sci. Technol 34:853-858.

276 Gashti MP, Pournaserani A, Ehsani H, Gashti, MP (2013a) Surface oxidation of
 277 cellulose by ozone-gas in a vacuum cylinder to improve the functionality of
 278 fluoromonomer. Vacuum 91:7-13.

279 Gashti MP, Elahi A, Gashti MP (2013b) UV radiation inducing succinic acid/silica -
 280 kaolinite network on cellulose fiber to improve the functionality. Composites
 281 Part B 48:158-166.

282 Gashti MP, Almasian A (2013) Citric acid/ZrO₂ nanocomposite inducing thermal
 283 barrier and self-cleaning properties on protein fibers. Composites Part B
 284 52:340-349.

285 Grancarić AM, Jerković I, Koncar V, Cochrane C, Kelly FM, Soulat D, Legrand X
 286 (2018) Conductive polymers for smart textile applications. J. Ind Text
 287 48:612-642.

288 Gu JF, Gorgutsa S, Skorobogatiy M (2010) Soft capacitor fibers using conductive
 289 polymers for electronic textiles. Smart Mater. Struct 19:1-13.

290 Huang G, Liu L, Wang R, Zhang J, Sun X, Peng H (2016) Smart color-changing
 291 textile with high contrast based on a single-sided conductive fabric. J. Mater.
 292 Chem. C 4:7589-7594.

293 Huang G, Gao J, Wang X, Liang H, Ge C (2012) How can graphene reduce the
 294 flammability of polymer nanocomposites?. Mater. Lett 66:187-189.

295 Hu G, Zhao C, Zhang S, Yang M, Wang Z (2006) Low percolation thresholds of
 296 electrical conductivity and rheology in poly (ethylene terephthalate) through the
 297 networks of multi-walled carbon nanotubes. Pol 47:480-488.

298 Huang G, Wang S, Song P, Wu C, Chen S, Wang X (2014) Combination effect of

299 carbon nanotubes with graphene on intumescent flame-retardant polypropylene
300 nanocomposites. *Composites. Part A* 59:18-25.

301 Liu S, Yan H, Fang Z, Wang H (2014) Effect of graphene nanosheets on morphology,
302 thermal stability and flame retardancy of epoxy resin. *Compos. Sci. Technol*
303 90:40-47.

304 Liu L, Chen Y, Liu H, Rehman HU, Chen C, Kang H, Li H (2019) A graphene oxide
305 and functionalized carbon nanotube based semi-open cellular network for sound
306 absorption. *Soft matter* 15:2269-2276.

307 Nooralian Z, Gashti MP, Ebrahimi I (2016) Fabrication of a multifunctional
308 graphene/polyvinylphosphonic acid/cotton nanocomposite via facile spray
309 layer-by-layer assembly. *RSC Adv* 6:23288-23299.

310 Palaskar S, Kale KH, Nadiger GS, Desai AN (2011) Dielectric barrier discharge
311 plasma induced surface modification of polyester/cotton blended fabrics to
312 impart water repellency using HMDSO. *J. Appl. Polym. Sci* 122:1092-1100.

313 Pan Y, Liu L, Wang X, Song L, Hu Y (2018) Hypophosphorous acid cross-linked
314 layer-by-layer assembly of green polyelectrolytes on polyester-cotton blend
315 fabrics for durable flame-retardant treatment. *Carbohydr Polym* 201:1-8.

316 Qing X, Wang Y, Zhang Y, Ding X, Zhong W, Wang D, Lu Z (2019) Wearable
317 Fiber-Based Organic Electrochemical Transistors as a Platform for Highly
318 Sensitive Dopamine Monitoring. *ACS Appl. Mater. Interfaces* 11:13105-13113.

319 Qu J, He N, Patil SV, Wang Y, Banerjee D Gao W (2019) Screen Printing of Graphene
320 Oxide Patterns onto Viscose Nonwovens with Tunable Penetration Depth and
321 Electrical Conductivity. *ACS Appl. Mater. Interfaces* 11:14944-14951.

322 Rahimi MH, Parvinzadeh M, Navid MY, Ahmadi S (2011) Thermal characterization

323 and flammability of polyester fiber coated with nonionic and cationic softeners. J.
324 Surfactants Deterg 14:595-603.

325 Ren H, Sun J, Wu B, Zhou Q (2007) Synthesis and properties of a
326 phosphorus-containing flame retardant epoxy resin based on bis-phenoxy
327 (3-hydroxy) phenyl phosphine oxide. Polym. Degrad. Stab 92:956-961.

328 Ren J, Wang C, Zhang X, Carey T, Chen K, Yin Y, Torrisi F (2017)
329 Environmentally-friendly conductive cotton fabric as flexible strain sensor based
330 on hot press reduced graphene oxide. Car 111:622-630.

331 Saxena S, Tyson TA, Shukla S, Negusse E, Chen H, Bai J (2011) Investigation of
332 structural and electronic properties of graphene oxide. Appl. Phys. Lett
333 99:1838-1845.

334 Simorangkir RB, Yang Y, Esselle KP, Zeb BA (2018) A. Method to realize robust
335 flexible electronically tunable antennas using polymer-embedded conductive
336 fabric. IEEE Trans. Antennas Propag 66:50-58.

337 Shin S, Jang J, Yoon SH, Mochida I (1997) A study on the effect of heat treatment on
338 functional groups of pitch based activated carbon fiber using FTIR. Car
339 35:1739-1743.

340 Stankovich S, Dikin DA, Piner RD, Kohlhaas KA, Kleinhammes A, Jia Y, Ruoff RS
341 (2007). Synthesis of graphene-based nanosheets via chemical reduction of
342 exfoliated graphite oxide. Car 45: 1558-1565.

343 Tian M, Hu, X Qu L, Du M, Zhu S, Sun Y, Han, G (2016) Ultraviolet protection
344 cotton fabric achieved via layer-by-layer self-assembly of graphene oxide and
345 chitosan. Appl Surf Sci 377:141-148.

- Voiry D, Yang J, Kupferberg J, Fullon R, Lee C, Jeong HY Chhowalla M (2016)
High-quality graphene via microwave reduction of solution-exfoliated graphene
oxide, *Science* 353:1413-1416
- Wang X, Song L, Yang H, Lu H, Hu Y (2011) Synergistic effect of graphene on
antidripping and fire resistance of intumescent flame-retardant poly (butylene
succinate) composites. *Ind. Eng. Chem. Res* 50:5376-5383.
- Yun Y, Hong W, Kim WJ, Jun Y, Kim BH (2013) A novel method for applying
reduced graphene oxide directly to electronic textiles from yarns to fabrics. *Adv.
Mater* 25:5701-5705.
- Zahid M, Papadopoulou EL, Athanassiou A, Bayer IS (2017) Strain-responsive
mercerized conductive cotton fabrics based on PEDOT: PSS/graphene. *Mater.
Des* 135:213-222.
- Zhang X, Shi M (2019) Flame Retardant Vinylon/Poly (m-phenylene isophthalamide)
Blended Fibers with Synergistic Flame Retardancy for Advanced Fireproof
Textiles. *J. Hazard. Mater* 365:9-15.
- Zhao H, Tian M, Hao Y, Qu L, Zhu S, Chen S (2018) Fast and facile graphene oxide
grafting on hydrophobic polyamide fabric via electrophoretic deposition route. *J.
Mater. Sci* 53:9504-9520.