Review of Concrete Resistance to Abrasion by Waterborne Solids

DOI:
[10.14359/51724592](https://doi.org/10.14359/51724592)

Document Version
Accepted author manuscript

[Link to publication record in Manchester Research Explorer](#)

Citation for published version (APA):
Omoding, N., Cunningham, L., & Lane-Serff, G. F. (2020). Review of Concrete Resistance to Abrasion by Waterborne Solids. *ACI Materials Journal*, 117(3), 41-52. <https://doi.org/10.14359/51724592>

Published in:
ACI Materials Journal

Citing this paper
Please note that where the full-text provided on Manchester Research Explorer is the Author Accepted Manuscript or Proof version this may differ from the final Published version. If citing, it is advised that you check and use the publisher's definitive version.

General rights
Copyright and moral rights for the publications made accessible in the Research Explorer are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

Takedown policy
If you believe that this document breaches copyright please refer to the University of Manchester's Takedown Procedures [<http://man.ac.uk/04Y6Bo>] or contact uml.scholarlycommunications@manchester.ac.uk providing relevant details, so we can investigate your claim.

REVIEW OF CONCRETE RESISTANCE TO ABRASION BY WATERBORNE SOLIDS

Nicholas Omoding, Lee S. Cunningham, Gregory F. Lane-Serff

Biography: **Nicholas Omoding** is a PhD student at the Department of Mechanical, Aerospace and Civil Engineering (MACE), University of Manchester. His research interests include concrete durability and behavior of fiber reinforced composite structures.

Lee S. Cunningham is a Senior Lecturer at the Department of MACE, University of Manchester. He received his MEng from the University of Strathclyde and PhD from the University of Glasgow. His research interests include concrete performance in marine environments, design of reinforced concrete structures, fluid-structure interaction and structural composites.

Gregory F. Lane-Serff is a Senior Lecturer at the Department of MACE, University of Manchester. He received his BA and PhD from the University of Cambridge. His research interests include mathematical and experimental modelling of environmental flows.

ABSTRACT

In the last four decades, numerous investigations have been undertaken on abrasion-erosion of concrete using various test methods. These have suggested existence of different abrasion mechanisms, limitations of existing test methods and inconsistencies on the importance of compressive strength to abrasion resistance of concrete. The objective of this review is to: understand the mechanisms of concrete abrasion-erosion, assess the suitability of existing test methods to simulate field conditions and investigate the relationship between abrasion resistance and compressive strength. It is found that concrete abrasion mechanisms are dependent on both transport modes of abrasive charge and the ratio of coarse aggregate to matrix hardness. The ASTM C1138 (underwater) test method appears to simulate all the

critical modes of sediment induced abrasion expected in field conditions and specific energy can be used as a framework to correlate ASTM C1138 test results with field measurements. With the exception of concrete with rubber aggregates, abrasion loss is found to fit a simple power function of its compressive strength, and no significant improvements in abrasion resistance can be gained by using concretes with compressive strengths exceeding 60 MPa (8.70 ksi). Also, the influence of cementitious additives and coarse aggregate properties is only significant at compressive strengths below the optimal value of 60MPa (8.70 ksi).

Keywords: concrete abrasion; coastal structures; durability; hydraulic structures; resistance models

INTRODUCTION

Abrasion-erosion is a major form of deterioration in concrete structures exposed to the action of water flows incorporating hard sediments. Although silt and sand sediments can also cause some degree of concrete abrasion-erosion damage, severe damage occurs when coarse sediments defined on the Wentworth scale¹ as pebbles (2-64 mm [0.0788-2.520 in.]) and cobbles (64-256 mm [2.520-10.086 in.]) are transported at velocity by the flow^{2,3}. Its effects on structural performance include reduced safety, reduced durability and increased operating costs arising from regular repair requirements. Many past studies summarised in the recent report of ACI Committee 207⁴ have strongly focused on abrasion-erosion of stilling basins of hydro-electric dams and other riverine structures for which abrasion loss depths of up to 2 to 3 m (6 to 10 ft.) have been reported. However, this type of damage also poses serious maintenance challenges for concrete structures situated in the coastal environment with coarse beach sediments^{2,3}. **Figure 1** shows a revetment-seawall junction at Rossall, Fleetwood in the North West of England exhibiting severe abrasion-erosion with exposed steel reinforcement and sheet piles which are also heavily abraded. This particular damage

was caused by the action of rounded pebbles and cobbles (also termed as shingle) driven by breaking ocean waves³. Indeed, the exposure of embedded metal components creates suitable conditions for the onset of secondary structural degradation processes such as chloride-induced corrosion³. Concrete abrasion-erosion depths shown in **Table 1** underscore the significance of this problem in coastal structures. In fact, for both stilling basins and coastal structures constructed in severe abrasive environments, attainment of the typical 100 year design service life can be jeopardised, more so in the absence of a robust maintenance programme. Furthermore, the fact that repair of abrasion-damaged surfaces are expensive operations costing millions of dollars⁵ exacerbates the consequences of abrasion-erosion.

When abrasion-damage in stilling basins was arguably first problematized in the USA in the 1950s⁶, damaged surfaces were repaired using various materials without any evaluation of their relative abrasion performance. The repair materials used included conventional, fibre-reinforced, and polymer-impregnated concretes. As expected, the different repair materials used exhibited markedly varied degrees of effectiveness⁵. These findings highlighted the importance of developing laboratory test methods for rapidly evaluating the relative performance of materials proposed for construction or repair of hydraulic structures⁵.

In the last four decades, several test methods outlined in **Table 2** have been developed, and used in numerous studies to investigate concrete abrasion mechanisms and influencing factors. These investigations have suggested different mechanisms that are dependent on the nature of interaction of the abrasive solid and the surface, and also yield a plethora of possible governing parameters. In particular, there have been contradicting conclusions regarding the relationship between the compressive strength and abrasion resistance as summarised in **Table 3**.

The objective of this review is to examine published research to: (a) investigate mechanisms

1 of concrete abrasion by waterborne solids; (b) evaluate existing laboratory test methods for
2 concrete abrasion-erosion; (c) examine the relationship between concrete abrasion resistance
3 and compressive strength by evaluating existing experimental test data.

4 The structure of the paper is such that mechanisms of concrete abrasion-erosion are first
5 discussed together with conclusions drawn from other cementitious composites and brittle
6 materials. Existing laboratory test methods for abrasion-erosion are then evaluated and
7 plausible methods for relating laboratory test results to field performance recommended.
8 Finally, approaches to modelling abrasion/erosion resistance of concrete and other brittle
9 materials are covered and existing experimental test data used to investigate relations
10 between abrasion-erosion and compressive strength.

11 **RESEARCH SIGNIFICANCE**

12 Abrasion-erosion resistance is an important requirement for concrete mixtures used in the
13 construction and repair of concrete structures exposed to action of hard waterborne
14 sediments. The understanding of concrete abrasion-erosion mechanisms, suitability of
15 existing test methods and establishment of a relationship between abrasion resistance and
16 compressive strength that accounts for abrasion mechanisms are valuable for assessment of
17 the relative performance concrete mixtures without recourse to costly experimental
18 campaigns. This can also be useful in the specification of abrasion resistant concrete mixtures
19 for construction and repair of hydraulic structures, hence improving the durability of both
20 new and repaired surfaces.

21 **MECHANISMS OF CONCRETE ABRASION-EROSION**

22 In order to understand the mechanisms of concrete abrasion, it is important to recognise that
23 concrete is a brittle material. Erosion in brittle materials is mostly influenced by their
24 composition and modes of transportation of abrasive solids. In heterogeneous brittle materials

such as cement pastes which are essentially a conglomerate of small grains held together by hydraulic and chemical bonds, Bitter⁷ suggests that under impact action, individual grains are dislodged in their entirety through rupture of the bonds holding them together. The resistance of these types of materials to abrasion therefore is largely determined by the strength of the inter-granular bonds rather than that of the grains themselves. This is in contrast with homogeneous materials like glass whereby the action of low velocity solids creates stress concentrations that cause cracking at a depth that is related to the size of impacting solids. At high velocities of solids however, the crack direction is determined by particle velocity⁷.

In conditions whereby rolling is the dominant transport mode of the solids, Rabinowicz⁸ states that material failure occurs due to a phenomenon called surface contact fatigue. This type of failure is related to general fatigue in that contacting material stresses and the number of cycles required to cause failure have a characteristic relationship⁸. Vassou et al.⁹ arrived at the same conclusion after microstructural examination of concrete specimens with compressive strength ranging from 42 to 64.5 MPa (6.1 to 9.4 ksi) abraded by a rotating wheel apparatus. Petrographic examinations revealed that there were numerous cracks beneath the abraded surfaces when compared to the degree of inherent micro-cracking in concrete. This indicates that eventual spalling of surface material is attributable to the development, growth and intersection of surface and sub-surface cracks⁹. Microcracks can develop in any of the concrete phases i.e. coarse aggregate, bulk matrix and interfacial transition zone (boundary between cement paste and aggregates) depending on their relative strengths¹⁰. The interfacial transition zone (ITZ) is the most vulnerable phase for initiation of cracking in concrete owing to its relatively low hardness based on micro-indentation tests carried out by Sonebi¹¹.

Several researchers^{9,12-15} attribute surface and sub-surface micro-cracking during the abrasion

process of brittle materials to development of tensile and shear stresses respectively. These conclusions are based on Hertz's equations¹³ for elastic contact between solid bodies. Hertz's equations show that peak tensile stresses at the surface act radially round the periphery of the contact area of the solid while shear stresses are highest at a depth of about half the radius of the contact circle^{13,14}. Therefore, while contact mechanics can be applied for prediction of material fracture initiation due to the action of solids^{9,14,16,17}, the ensuing processes after this has occurred are not understood. The material failure process can further be complicated in concrete if hard aggregate debris plucked from the surface is present between the eroded surface and abrasive solid due to the on-set of a secondary wear mechanism called three-body abrasion⁹. Finnie¹⁵ and Vassou et al.⁹ have respectively suggested that material removal in ceramic and concrete surfaces results from the alteration in direction of crack propagation and/or interaction of cracks oriented in different directions. This can for example occur by vertical deflection of originally horizontal (parallel to the surface) cracks as well as by intersection of horizontal and vertical cracks (perpendicular to the surface)^{9,17} followed by the isolated debris being plucked off the surface. Mechanisms consistent with this have also been reported in rocks subjected to impact by low-velocity solids¹⁷. Further, it has been established that the ratio of coarse aggregate to matrix hardness influences the mechanism of concrete abrasion³. In concrete mixtures where the hardness of the matrix is lower than that of coarse aggregates, the former wears out at a relatively faster rate leaving the latter protruding, and thus susceptible to plucking off the surface. However, when coarse aggregate and matrix hardness are comparable, uniform wear of the two phases is exhibited and plucking of coarse aggregates is unlikely to occur. The two scenarios are illustrated in **Figure 2**.

The strength of the ITZ, whose width typically ranges from 40 to 90 μm (1.575 to 3.543×10^{-3} in.)^{11,18}, influences the plucking of coarse aggregates in concretes designed with low ratios

of matrix to coarse aggregate hardness.

It is thus observed that there is consensus in the explanation of abrasion failure initiation in brittle materials like glass, rock, cement pastes, ceramics etc. In concrete however, the understanding of fracture initiation and subsequent material removal processes is complicated by its multi-phase structure for which the material phase for failure initiation becomes highly probabilistic. It is also clear that concrete abrasion mechanisms influence abrasion-erosion rates. For concrete mixtures susceptible to plucking of coarse aggregates, knowledge of threshold conditions for the onset of this phenomenon are critical for reliable prediction of abrasion losses, expected to be a function of coarse aggregate (CA) grading. In fact, the maximum size of material removable in a single impact should be a function of the maximum size of CA. In contrast, abrasion loss suffered by concrete mixtures with comparable coarse aggregate and matrix hardness should not be related to CA grading.

EVOLUTION OF LABORATORY TEST METHODS

An evaluation by Liu⁵ in 1980 of the rubbing, dressing wheel, ball bearing, shot-blast and rattler-type apparatus concluded that none was suitable for testing abrasion resistance of concrete exposed to sediment-laden flows. This evaluation formed the basis for the development of the underwater test¹⁹, later standardised as ASTM C1138²⁰ for accelerated assessment of relative performance of different concrete mixtures. This implies that abrasion resistance indices from this test have no direct relation with concrete performance in actual field conditions. Subsequently, other test methods^{21–23} have also been developed in an attempt to address perceived limitations of the ASTM C1138 test.

ASTM C1138 (Underwater) test method

The underwater test involves submersion of a disc-shaped concrete specimen of about 300 mm (11.82 in.) diameter and 100 mm (3.94 in.) thickness in water contained in a 300mm

diameter steel cylinder. The sample is abraded by 70 steel balls of three different diameters (25 of 0.5 in. [13 mm], 35 of 0.75 in. [19 mm] and 10 of 1.0 in. [25 mm]). The motion of the steel balls is caused by agitation of water by an immersed paddle rotating at speed of 1200 rpm. Concrete abrasion loss is then measured at 12-hour intervals over a total duration of up to 72 hours²⁰ and reported as a percentage of mass of the specimen before the test. For high-strength concretes (HSC), considered as those with compressive strengths exceeding of 55 MPa (7.977 ksi)²⁴, sufficient abrasion may not be achieved within the standard 72 hours to be able to distinguish their relative performance. However, test durations of up to 120 hours have proven successful in the evaluation of HSC^{25,26}.

The reliability of any laboratory test method for investigating a physical phenomenon is greatly determined by its ability to adequately simulate the actual conditions. In the case of abrasion-erosion in the field environment, abrasive sediment transport occurs as either bedload or suspended load. The behaviour exhibited by sediments moved as the former and latter is respectively influenced by flow-induced boundary shear stress on the sediment grains²⁷ and flow turbulence²⁸. Bed load is the proportion of the total sediment load that is in constant contact with the exposed surface and moves either by rolling, sliding or saltation²⁸ and is thought to be responsible for most of the wear inflicted on exposed surfaces. Some researchers^{19,22,29,30} have argued that steel ball motion in the ASTM C1138 test occurs by rolling and sliding only due to the inability of the paddle agitation speed to lift steel balls off the concrete surface. This has been stated as the main limitation of this method since the impact component of wear resulting from saltation motion of steel balls may not be produced. These assertions directly contradict with similarities observed between laboratory and field abraded surfaces of both stilling basins of hydro-electric dams^{19,29} and coastal defence elements³. **Figure 3** shows a stepped revetment armour unit abraded in field conditions at the

beach in Cleveleys on the Fylde Peninsula, Lancashire, England and a concrete disc from the same mixture tested in the laboratory using the ASTM C1138 method. For laboratory damaged concrete surfaces to show similarity with those observed in field conditions where all modes of motion to occur including impact, it implies that either some degree of impact action takes place during the underwater test or it is of little significance in the abrasion-erosion of both coastal revetments and stilling basins. It is hypothesised that the similarity in abraded surfaces is because of the former. However, saltation action is not induced by paddle agitation alone; it is in combination with surface roughness which occurs after the removal of the surface matrix. Also, flow vortices generated near the rough surface contribute to the intensity of the impact action thus enabling the ASTM C1138 test method to simulate all the relevant modes of sediment transport occurring in field conditions. Despite its limitations, the ASTM C1138 test appears to be the most reliable method for assessing concrete abrasion-erosion in flows whereby sediments are mainly transported as bedload.

Other existing test methods

The suggested limitations of the ASTM C1138 test discussed have led to efforts to develop alternative test methods for concrete abrasion. The Chinese test code of hydraulic concrete²¹ proposes the ring method as a robust alternative capable of simulating actual modes of sediment motion including impact action²². In this test, the mixture of water and abrasive solid (0.4 to 2 mm [0.0158-0.0788 in.]) at a concentration of 20% is contained in the annulus of the sample. The mixture is moved in rotary and eddying motion by an electric motor-driven agitation paddle rotating at a speed of 14 m/s (2700 rpm). This causes abrasion of vertical surfaces of the annulus which is measured at intervals of 15 minutes over a total duration of 60 minutes. The abrasion-erosion of concrete is then reported as rate of mass loss per unit area²². Based on the size of abrasive sediments used, the ring test appears to be most

1 suited for the evaluation of concrete abrasion-erosion by fine sediments. Horszczaruk²³ also
2 proposed an alternative test method that involves rotating concrete samples that are radially
3 attached to an axle in a horizontally oriented drum containing water and natural aggregates
4 mixture. The size of pebbles used as abrasive charge was 8-32 mm (0.315-1.261 in.) and
5 constituted 33% (by volume) of the total mixture. The concrete samples were abraded for a
6 total duration of 96 hours and abrasion reported as percent mass loss²³.

7 It is evident that all the three described test methods are similar in principle and involve
8 agitation of water-sediment mixture to cause abrasion of concrete surfaces. Abrasion loss
9 measurements are taken at intervals for durations of up to 120 hours depending on the resistance
10 of the concrete mixtures under evaluation. The ASTM C1138 and ring methods comprise of
11 simple apparatus to fabricate hence suited for rapid, economical and repeatable evaluation of
12 concrete performance whilst the rotating drum method is disadvantaged by its bulky set-up.

13 Among all methods covered, the underwater test has by far gained wide acceptability as the
14 most suitable method for evaluation of concrete resistance to abrasion by waterborne solids.
15 This is confirmed by its standardisation as ASTM C1138²⁰ and adoption by the Chinese test
16 code for hydraulic concrete²¹.

17 **FIELD APPLICATION OF ASTM C1138 TEST RESULTS**

18 There have been few research attempts to correlate ASTM C1138 findings with field
19 performance. Horszczaruk³¹ investigated the influence of the abrasive environment on the
20 abrasion of a constant concrete mixture with a compressive strength of 127.9 MPa (18.55 ksi)
21 and water to cementitious material ratio of 0.272 by varying the rotation speed of the
22 agitation paddle. The concrete mixture was produced from cement type CEM 1 52.5R, silica
23 fume, natural sand FA and basalt CA with a maximum size of 16 mm. The cement, silica
24 fume, FA and CA contents were 450, 45, 630 and 1279 kg/m³ (759, 76, 1062, 2156 lb/yd³)

respectively. The study used the steel ball sizes and quantities specified in ASTM C1138²⁰ and concrete abrasion loss was measured at paddle rotation speeds of 350, 540, 970 and 1200 rpm. Based on the test results, a concrete abrasion loss (A_L) model was proposed as a function of paddle agitation speed (v_r) and exposure duration (t) as:

$$A_L(v_r, t) = \beta_1 v_r \ln(t + 1)^{\beta_2} v_r^{\beta_3}, \quad (1)$$

where, β_1 , β_2 and β_3 are regression coefficients valid for the concrete mixture tested only. This limits the practical application of this model. Kryžanowski et al.³⁰ later proposed a more plausible framework for relating laboratory test results and field measurements using an energy-based approach. This entails quantification of specific of energy of steel balls in the standard underwater test and abrasive sediments in the field environment. The specific energy ratio is then used to estimate the equivalent duration of the accelerated underwater test for the exposure period in field conditions. This approach has been validated for a stilling basin with field (flow speed of 20 m/s [65.6 ft./s]) to laboratory (flow speed of 1.8 m/s [5.9 ft./s])¹⁹ specific energy ratio of 1:10. However, the assumption that the abrasive charge is transported at the speed of water is a limitation common to models proposed by both Horszczaruk³¹ and Kryžanowski et al.³⁰. This is because whilst flow velocity is one of the key parameters that determine the velocity of abrasive sediments, there is a multitude of other variables that influence it such as properties of the solids, intensity of sediment collisions, surface roughness etc. Therefore, a more robust approach would be to establish the specific energy based on the actual velocity of the abrasive charge in both laboratory and field conditions. Sediment velocity in the field can be estimated from scaled models of particular applications. Nonetheless, it can be stated that progress has been made in formulating approaches for relating laboratory and field abrasion measurements. However, development of reliable models for the prediction of concrete performance in field conditions from laboratory

measurements will require adequate understanding of the actual motion of the abrasive sediments rather than water flow velocities as currently proposed.

CONCRETE ABRASION RESISTANCE MODELLING

The development of a reliable model for concrete resistance to abrasion-erosion requires knowledge of its governing parameters. Whilst hardness has been successfully used to model wear resistance of metals, the composite nature of concrete in which the respective phases exhibit varying hardness levels complicates its application. Evidently, owing to lack of agreement among researchers on an abrasion resistance parameter for concrete, different but logical proposals include use of strain energy and correlations to compressive strength.

Erosion strength concept

Thiruvengadam³² proposed the concept of erosion strength to be applicable to any material. In this approach, it is assumed that erosion of any solid surface results from the energy supplied by erosive agents and whilst a fraction of this energy is absorbed by the exposed material some is lost for instance as heat. The amount of energy absorbed by the material depends on its absorption efficiency⁴. The relationship between energy absorbed by an eroded volume of material and its erosion strength is expressed by **Equation (2)**.

$$E_a = \Delta V \cdot S_e, \quad (2)$$

where,

E_a = energy absorbed by the eroded material;

ΔV = volume eroded material; and

S_e = erosion strength of the material.

In **Equation 2**, ΔV can be assessed by existing laboratory techniques such as the underwater test but calculation of S_e requires knowledge of the energy absorbed by the eroded material.

Thiruvengadam³² demonstrated the application of the erosion strength concept using

cavitation-erosion of metals whose erosion resistance was proportional to their strain energy. The rate of energy absorption per unit area, also referred to as the intensity of erosion (I) is obtained from **Equation (3)**.

$$I = h \cdot \frac{S_e}{t}, \quad (3)$$

where,

t = test duration; and

h = average depth of erosion.

In the cavitation-erosion case, test results of the stated metals were used to determine the intensity of a given test device over a range of test conditions by assuming that their erosion strength is identical to strain energy. This process is essentially a calibration of the erosion test apparatus to determine its intensity. The calibrated device can then be used to assess the resistance of any material to erosion based on the rate of increase in erosion depth³².

Although this approach has been suggested to be valid for other materials and cases of solids-impact erosion and friction wear, it has only been verified for cavitation-erosion of metals.

The scarcity of experimental test data in which concrete abrasion loss is related to its strain energy makes it difficult to confirm the applicability of this concept in concrete subjected to action of waterborne solids. However, Engle³³ lends it considerable credibility for application to concrete in abrasive conditions based on theoretical analysis. This analysis proves that for brittle materials such as glass, graphite and hardened steel, impact erosion resistance (R) and strain energy estimated at their flexural strength is expressed by **Equation (4)**.

$$R \approx \frac{\sigma_b^2}{E^{0.5}} \quad (4)$$

where,

E = elastic modulus; and

1 σ_b = flexural strength of the material.

2 Similarly, Sklar and Dietrich¹⁷ expressed erosion resistance of rock to incision by saltating
3 sediments in river flow conditions as a function of its elastic modulus and tensile strength.
4 This was derived by expressing the erosion resistance as energy required for abrasion of a
5 unit volume of rock. This energy was taken to be directly and inversely proportional to the
6 square of rock tensile strength and elastic modulus respectively. This suggests that brittle
7 materials with high tensile strength and low elastic modulus exhibit better abrasion
8 performance.

9 **Compressive strength**

10 Studies that have reported abrasion-erosion loss together with tensile strength and elastic
11 modulus are scarce, however, empirical relations have been proposed over the years for
12 evaluation of both tensile strength^{34,35} and elastic modulus³⁶ of concrete from its compressive
13 strength. A comprehensive review by Oloukun³⁵ showed that researchers agree that tensile
14 strength of concrete has a power relation ranging from 0.6 to 0.8 with cylinder compressive
15 strength. BS EN 1992³⁷ provides a relation for estimating elastic modulus from compressive
16 strength only, and more recently, Noguchi et al.³⁶ analysed a large test dataset and concluded
17 that elastic modulus of concrete can be more reliably predicted using compressive strength
18 and unit weight. If these relations are considered together with **Equation (5)**, it becomes
19 apparent that abrasion-erosion resistance (R), at least for conventional concretes, should be
20 related to its compressive strength (f_c). Defining R as the inverse of percentage abrasion mass
21 loss (A_L), the generic resistance model based on compressive strength can be expressed as:

$$A_L = \beta f_c^{-\alpha}. \quad (5)$$

23 where, β and α are regression coefficients that can be obtained from experimental data.

24 Most investigations with conventional concrete mixtures undertaken with ASTM C1138 test

method have often concluded that abrasion resistance improves with increase in compressive strength but concretes incorporating rubber aggregates^{22,29}, and those with relatively high proportions of coarse aggregates³ do not follow this trend. In fact, concrete mixtures with rubber aggregates exhibit high abrasion resistance at increased rubber aggregate contents which are also accompanied by reductions in compressive strength. Furthermore, even for conventional concrete mixtures, abrasion-erosion resistance is not infinitely enhanced by compressive strength increase. This suggests the presence of an optimum value beyond which no significant improvements in abrasion resistance are accrued by increasing compressive strength. The range of optimum compressive strength value on abrasion resistance and the influence of concrete mixture design parameters can be examined by evaluating published ASTM C1138 test results.

EVALUATION OF EXISTING EXPERIMENTAL TEST DATA

The sources for the experimental test data analysed and critical mixture design parameters for the concretes are summarized in **Appendix A**. The data covers cube compressive strengths ranging from 23 MPa to 128 MPa (3.336 to 18.565 ksi), different water to cementitious materials ratios, aggregates types and grading. The influence of the curing regime used and age of the test specimen of 7 to 182 days are also accounted for. This represents the total set of available ASTM C1138 test data published over the last 38 years and takes into consideration the variability in concrete composition and properties that can reasonably be expected in practice. It should be noted that fibre-reinforced concretes (FRC) are out of scope of this evaluation. This is due to the fact that fibre addition can either favourably or adversely influence abrasion-erosion resistance of concrete depending on their type, size, shape quantity etc. In concrete, there is evidence that fibre addition can either reduce or increase abrasion-erosion resistance by up to 60% and 49% respectively^{25,26,29,38,39} while in mortars,

adverse effects on abrasion resistance of up to 87%⁴⁰ and enhancements of up to 68%^{41,42} have been reported. These effects which depend on the fibre types and dosages used can significantly increase the scatter of the data points making comparative analysis difficult. Therefore, it is more rational to first establish a general formula for assessing abrasion resistance for basic concrete mixtures to which correction factors can be applied to cater for the effect of fibre addition.

It is observed that specimens for compressive strength test used by different researchers have inevitably been variable in shape and size. Concrete cylinders (150 ϕ /300 mm and 100 ϕ /200 mm) and cubes (150 and 100 mm sides) have all been used in literature. These have been transformed into compressive strengths of equivalent 150 mm cubes (reference specimen) based on the relations provided in BS EN 206⁴³ and Neville⁴⁴. Similarly, abrasion losses reported as either depth of damage, mass in grams, volume or in combinations were converted to per cent mass loss prior to overall analysis. Although ASTM C779-Procedure C⁴⁵ test does not adequately model abrasion action of water-borne sediments, its results have been used to qualitative comparison with those of ASTM C1138 test²⁰ to assess the consistency of the effects of the parameters evaluated.

Influence of compressive strength

The relationship between cube compressive strength on the 72-hour concrete abrasion loss was evaluated using ASTM C1138 test results by Liu¹⁹, Smoak et al.⁴⁶, Nazari and Riahi⁴⁷, Rashwan and Abou-Zeid⁴⁸, Horszczaruk^{25,31,49,50}, Cunningham et al.³, Wang et al.⁵¹, Sonebi and Khayat²⁶, Kang et al.²² for non-fibre reinforced concrete mixtures produced with conventional coarse aggregates (CA) of known rock types. For completeness, underwater test results in which the rock types used in the CA were insufficiently described as either natural gravel⁴⁹, crushed stone^{39,52,53} or marginal⁵⁴ aggregates were also considered. In the test data

where mineralogical descriptions of CA have been provided, these can generally be categorised into basalt^{3,19,25,31,47,48,50}, granite^{19,26,48,51}, limestone^{19,22,26} and dolomite⁴⁸. **Figure 4** shows the variation of 72-hour abrasion loss with compressive strength. **Figure 4** generally indicates that concrete abrasion resistance initially improves with increased compressive strength until an optimum compressive strength is attained beyond which further increase does not yield any significant abrasion resistance improvements. In fact, for the conventional concrete mixtures analysed, the optimum compressive strength for 72-hour abrasion resistance ranges from 60 to 70 MPa (8.70-10.15 ksi) regardless of the concrete composition. This optimum range is important because in exposure environments where abrasion is the governing parameter in the specification of concrete, the use of ultra-high-strength concretes can be avoided thus optimising the cost of concrete. The minimum compressive strength of concrete used in abrasive conditions is normally specified in design codes based on both durability and strength requirements. The optimal compressive strength range for abrasion resistance obtained complies with the requirements of BS 6349⁵⁵ which specifies the minimum cylinder/cube strength of 40/50 MPa (5.80/7.25 ksi) for abrasive maritime conditions. All concretes currently in use in hydraulic structures, including ultra-high strength types suffer some degree of damage in abrasive conditions hence abrasion loss cannot be zero, implying that a practical predictive curve will be asymptotic to the abrasion loss (A_L) and compressive strength (f_c) axes as exhibited in **Figures 4**. This is an indication that concrete abrasion loss as a function of compressive strength can generally be represented by a simple power relation rather than complicated polynomial functions suggested by some researchers^{26,50}. The equation shown in figure 4, which was obtained from regression analysis, results in a reasonable lower bound prediction for compression strengths of 60 MPa and greater. The low co-efficient of determination (24.6%) is due to the large scatter in test

data observed at compressive strengths of less than 60 MPa (8.70 ksi) and is evidence of the significance of concrete mixture additives on abrasion resistance at these strengths. This equation requires improvement to account for the effect of rubber aggregates, coarse aggregate type etc. and introduction of supplementary cementitious materials (silica fume, nano-particles, fly ash and ground granulated blast-furnace slag) as examined next.

Influence rubber aggregate addition

Test results from ASTM C1138 and ring methods^{22,29,30} show that concretes with rubber aggregate exhibit remarkably high abrasion resistance in spite of compressive strength reduction. The details of concrete mixtures considered can be found in the stated references. Kang et al.²² reported 225% enhancement in 72-hour ASTM C1138 abrasion resistance at 28 days due to addition of 15% crumb rubber aggregates. This is consistent with results of Kryžanowski et al.^{29,30} who also showed that replacement of sand with 9.5% fine rubber aggregates improved abrasion resistance by over 200% and 300% at 90 and 900 days of curing. The mechanisms by which rubber aggregates improve concrete abrasion resistance are not well understood but Finnie¹⁵ notes that low elastic modulus and large Poisson's ratio of about 0.5 make rubber materials more erosion resistant. This is attributed to the reduced tensile contact stresses which minimises the risk of crack initiation and propagation²². However, despite the superior performance of rubberised materials in both laboratory^{22,29,30} and field^{29,30} test conditions, there are legitimate concerns with regards to their long-term performance, aesthetics and environmental impact⁵⁶. Specifically, degradation by biological, chemical and ultraviolet light as well as effects of rubber particles on river and marine life are some of the areas that need further clarification.

Influence of coarse aggregate hardness

Figure 4 shows that at comparable compressive strengths, concretes produced with coarse

aggregates (CA) from different rocks performed variously in the ASTM C1138 test. Concretes produced from coarse aggregates (CA) with relatively high hardness like basalt are exhibit superior abrasion resistance than those with low hardness values such as limestone^{3,19,57}. This indicates that the hardness of CA used which is mainly influenced by the mineralogical composition of the parent rock is an important factor in the abrasion resistance of concrete once exposed. Although generally defined as a measure of the material's resistance to plastic deformation⁸, quantitative values of hardness are in fact meaningless unless the test method used for their measurement is stated. There is no unanimity in the literature on the best test method for CA hardness for concrete used in abrasive conditions and as such, previous researchers have adopted Los Angeles (LA) abrasion^{19,54}, Micro Deval³ and Mohs¹⁹ hardness tests methods albeit with varied degrees of success. Liu¹⁹ and Kumar and Sharma⁵⁴ concluded that there was no correlation between concrete abrasion loss measured by the underwater test method and coarse aggregate LA abrasion losses. Unfortunately, published test data on the variation of underwater abrasion loss with the Micro Deval values of CA is very limited for meaningful conclusions to be drawn. However, a strong relation has been reported between CA Mohs hardness number and underwater concrete abrasion losses¹⁹. Although Mohs hardness test is only qualitative in nature, empirical evidence exists showing that for minerals, it can be related to other improved hardness tests such as Vickers micro-indentation hardness⁵⁸. According to Craig and Vaughan⁵⁹, Vickers micro-indentation hardness (VHN) of minerals has a linear/logarithmic variation with Mohs hardness scale and the relation in **Equation (6)** has been suggested by Young and Millman⁶⁰.

$$\log VHN = 2.5 \log Mohs + 1.00. \quad (6)$$

Vassou et al.⁹ provide further evidence of potential relevance of micro-indentation hardness

techniques in assessing abrasion resistance for applications where the interaction between abrasive solids and exposed surfaces is by rolling contact. Although Vassou et al.⁹ focused on the characterisation of the finished surface micro-structure made up of the matrix phase, the strong correlations obtained between micro-indentation hardness and abrasion loss is also confirmation that scratch-based methods are suitable for measurement of hardness of both CA and matrix phases of concrete. This suggests that recent advances in nano-scratch methods which have proven successful in the measurement of hardness of cement pastes⁶¹ and concrete⁶² need to be exploited for evaluation of matrix and CA phases of concrete. Other aggregate-related properties reported to influence abrasion-erosion rates in concrete include the quantity and grading of coarse aggregates. Choi and Bolander⁶³ observed improved abrasion resistance at high ratios of exposed coarse aggregates to total surface areas while Cunningham et al.³ found that concrete mixtures with a high concentration of coarse aggregate experience high abrasion rates due to the poor degree of particle packing.

Influence of supplementary cementitious materials

The use of additives in the design of concrete and mortar mixtures aims to improve their properties in fresh and hardened states, and achieve environmental sustainability by using recycled waste. Concrete additives investigated for abrasion performance include: silica fume, nano-particles, fly ash, ground granulated blast-furnace slag.

Silica fume

Silica fume is the most popular additive used in the design of high-strength concretes⁶⁴ and silicon dioxide makes up about 90% of its composition⁶⁵. ACI Committee 234⁶⁶ report provides comprehensive guidance on the use of silica fume in concrete. Test results by Kang et al.²² at 72-hours using ASTM C1138 showed addition of silica fume to concrete at a dose of 7% of the cement content improved its abrasion resistance and compressive strength by

86% and 29% respectively. In this study however, addition of silica fume without any adjustment in cement content also resulted in 7.5% reduction in the water to binder ratio in comparison to the reference mixture. Kumar and Sharma⁵⁴ also reported abrasion resistance improvements of 14 to 16% and 26 to 40% for ordinary Portland and Portland Pozzolana cement concretes respectively after introduction silica fume at a concentration of 10% of cement content. However, maximum compressive strength increases for both cement types was only 3.2%. Other researchers^{25,26,31,39,50} have also tested abrasion resistance of concretes with silica fume but have not provided reference mixtures for comparative analysis.

The results of ASTM C1138 tests are consistent with those of Ghafoori and Diawara^{67,68} who investigated the effect of silica fume addition on the abrasion performance of concrete using ASTM C779-Procedure C⁴⁵. Ghafoori and Diawara⁶⁷ used concrete specimens produced from ordinary Portland cement, natural siliceous fine aggregates and crushed limestone coarse aggregates with a constant w/binder ratio of 0.325. The optimum silica fume dosage was confirmed to be 10% of the cement content being used as a replacement for FA for both compressive strength and abrasion resistance at the ages of 7, 28 and 91 days. For the standard test age of 28 days, enhancements in compressive strength resulting from silica fume addition were 25, 64, 42 and 25% for silica fume concentrations of 5, 10, 15 and 20% respectively. At the same respective silica fume dosages and age, abrasion performance improved by 32, 49, 42 and 25%. Similar improvements in compressive strength and abrasion resistance tests using ASTM C779-Procedure C were reported by Laplante et al.⁶⁹. Tests were carried out on a concrete mixture produced from granite and limestone CA with contents that ranged from 970 to 1010 kg/m³ (1635-1702 lb/yd³) and FA constituted 775-785 kg/m³ (1306-1323 lb/yd³). Ordinary Portland cement was used in all the mixtures with water to binder (cement + silica fume) ratio maintained at 0.48. The cement content ranged from 330-350

kg/m³ (556-590 lb/yd³) while a single silica fume dose of 8% by volume cement. The results showed that introduction of silica fume increased compressive strength of granite and limestone aggregate concrete by 38 and 53% respectively with only marginal improvements in abrasion resistance.

Based on the limited test data available, it is evident that silica fume addition generally improves abrasion resistance of concrete. Furthermore, the optimum dosage of about 10% of cement content which is recommended for compressive strength improvement⁶⁴ is also applicable to abrasion resistance. Ghafoori and Diawara⁶⁸ attribute the reduction in abrasion resistance in concrete mixtures with excessive silica fume concentrations to the depletion of the source of calcium hydroxide in concrete which stops the excess silica fume from reacting thus becoming just filler for microscopic voids. Therefore, silica fume dosages exceeding 10% of cement content can result in reduced abrasion resistance and increased costs of concrete. Importantly, there is a considerable difference in the degree of improvement in abrasion resistance and compressive strength for a given dose of silica fume. These differences should be accounted for in compressive strength-based abrasion resistance models using correction factors.

Use of nano-particles

While the typical average size of silica fume particles range from 0.1 to 0.2 μm (4 to 8×10^{-6} in.)⁶⁶, the effect of nano-particles with average sizes ranging from 10 to 15 nm (4 to 6×10^{-7} in) on abrasion resistance of concrete have also been a subject of previous studies^{47,70}. **Figure 4** shows that basalt CA concrete mixtures incorporating silicon dioxide (SiO_2) and aluminium oxide (Al_2O_3) nano-particles were superior in terms of abrasion resistance in comparison to mixtures of comparable compressive strengths without nano-particles⁴⁷. This is consistent with results reported by Li et al.⁷⁰ and obtained from ball bearing⁷¹ tests. In Li et al⁷⁰, the

concrete mixture used was produced using ordinary Portland cement, natural sand as FA and crushed diabase CA with a particle size range of 5-25 mm. The water to cement ratio was 0.42 while the FA constituted 34% of the total volume of the concrete mixture. Titanium dioxide (1%, 3% and 5%) and silicon dioxide (1% and 3%) nano-particles were introduced as percentages of cement content (by weight). The results showed that abrasion resistance of float-finished surfaces improved by 157.0% and 100.8% with 1% and 3% silicon dioxide nano-particles additions respectively. As-struck surfaces on the other hand experienced improvements of 139.4% and 89.0% for the same nano-particle dosages. In contrast, use of titanium dioxide nano particles yield much stronger improvements of 180.7%, 147.7% and 90.4% at respective dosages of 1%, 3% and 5% for the top trowelled surface and 173.3%, 140.2% and 86.0% for as-struck surfaces. The results indicate that the optimum amount of nano-particles for abrasion resistance to be less than 1% of the cement content. This improved abrasion resistance at relatively small doses of nano-particles has been attributed to the development of a more compact and homogeneous matrix phase⁴⁷.

Fly ash

Fly ash is often introduced into a concrete mixture to improve its resistance to sulphate attack, increase strength and pumpability⁶⁴. However, its presence in concrete can also impact on its abrasion-erosion performance. ASTM C1138 abrasion-erosion test results by Horszczaruk and Brzozowski⁴⁹ showed that replacement of 20% and 30% of cement content with fly ash from a fluidized bed improved abrasion-erosion by 9% and 20% respectively at the age of 28 days whilst 10% and 44% increase was achieved at 56 days. These fly ash dosages also resulted in improved compressive strength by about 27% and 30% at 28 and 56 days respectively. However, abrasion resistance and compressive strength gains began to be reversed when fly ash concentrations exceeded 30%. A similar study by Kumar and Sharma⁵⁴

1 in which fly ash replaced 40% of the cement content reported marginal increase and decrease
2 in abrasion resistance and compressive strength respectively of concrete made from relatively
3 hard (LA abrasion value <50%) CA. In contrast, concrete mixtures produced with relatively
4 soft (LA abrasion value >50%) CA exhibited 18% reduction in abrasion resistance which was
5 accompanied no change in its compressive strength at 28 days. An extensive investigation by
6 Yen et al.⁵² using Class F fly ash⁷² showed that 97% of test data with fly ash dosages of 20%
7 to 30% showed reductions in abrasion resistance that ranged from 9% to 152%. The
8 corresponding reductions in compressive strength exhibited in 85% of the test data ranged
9 from 1 to 31%. In concrete mixtures with 15% cement replacement with class F fly ash, it can
10 be noted that the use of fly ash either had no effect or was beneficial (by up to 30%) in terms
11 of abrasion resistance in 70% of the reported test data. At the same fly ash dosage, 50% of the
12 test data exhibited increased compressive strength by up to 19%.

13 It can be discerned that the effect of fly ash addition on its abrasion resistance depends on the
14 type of fly ash used, dosage as well as the properties of other concrete constituents. Concrete
15 mixtures incorporating fly ash obtained from a fluidized bed show consistent increase in both
16 abrasion resistance and compressive strength up to an optimum dosage of 30% above which
17 no further performance improvements are gained. The performance of concretes produced
18 with other types of fly ash is inconsistent but results suggest that adverse effect is apparent
19 when fly ash replacements exceed 15% of cement content. Furthermore, the degree of effect
20 on abrasion performance is markedly different from that of compressive strength. This can be
21 of significance if abrasion resistance of concretes is to be fitted to a function of compressive
22 strength.

23 ***Ground granulated blast-furnace slag***

24 Ground granulated blast-furnace slag (ggbs) is added to a concrete mixture to improve

1 workability, retard setting time and reduce heat of hydration as well as increase curing time in
2 fresh concrete whilst in hardened concrete, ggbs reduces permeability, increases strength,
3 improves resistance to sulphate attack, reduces the potential for alkali-silica reaction^{73,74} and
4 reduces chloride ion diffusivity⁷⁵. Kumar and Sharma⁵⁴ used the ASTM C1138 test method to
5 investigate the effect replacing 40% of ordinary Portland cement content with ggbs in two
6 concrete mixtures produced with CA of LA abrasion values of less than and greater than 50%
7 . The results showed that use of ggbs together with relatively hard aggregates based on LA
8 abrasion values improved abrasion resistance and compressive strength of concrete by 8%
9 and 1% respectively. There was no significant effect on both abrasion performance and
10 compressive strength for the concrete mixture produced with CA with LA abrasion value of
11 less than 50%. Some researchers^{75,76} have used other methods to test abrasion resistance of
12 concretes with ggbs. Fernandez and Malhotra⁷⁵ used ASTM C779-Procedure C to investigate
13 the influence of ggbs addition in dosages of 0, 25 and 50% of cement content on the abrasion
14 resistance of concrete. The concrete mixtures were produced with water to binder ratios of
15 0.45, 0.55 and 0.70, binder content of 198 to 336 kg/m³ (334-566 lb/yd³), and had a cylinder
16 compressive strength of 18.0-31.7 MPa (2.61-4.60 ksi) at 28 days. The CA used was crushed
17 limestone with a maximum size of 19 mm (1103- 1175 kg/m³ [1859-1981 lb/yd³]) whilst
18 natural sand was used as FA (666-759 kg/m³ [1123-1279 lb/yd³]). The investigation showed
19 that the introduction of ggbs reduced abrasion resistance and compressive strength of
20 concrete. By considering abrasion wear depths at 250 and 550 seconds of the test for
21 specimen tested at 300 days, it is clear that abrasion resistance reduced by 6 to 55% with
22 introduction of ggbs. The degree of abrasion resistance reduction increased with reduction in
23 water to binder ratio. The results also show that replacement of 25% of the cement content
24 with ggbs reduced the 28 day compressive strength by up to 8% while 50% replacement

yielded compressive strength reductions of 14-18%. Comparative strength reductions were also generally observed at 91 and 365 days with only modest strength enhancement of 4 to 9% respectively being reported in concrete mixtures having water to binder ratios of 0.70. Other materials have also been investigated for possible use in concretes exposed to abrasive conditions. A field study by Allen and Terret² using test coastal revetment panels showed that abrasion resistance of concrete produced with high-alumina cements (HAC) was higher than those from ordinary Portland cement and super-sulphated cements by 250% and 600% respectively. The high abrasion-erosion resistance of HAC concrete has not been fully explained but Scrivener et al.⁷⁷ suggest higher strength of the ITZ due to a combination of reduced porosity and improved mechanical interlock between the cement paste and aggregates. These are attributed to the diffusion of aluminate ions due to their relative high mobility in comparison to silica ions. Rice husk ash use in concrete to achieve environmental sustainability⁷⁸ has also been investigated using the sand-blasting method by Wada et al.⁷⁹. However, whilst these two materials have potential use in abrasion-resistant concrete, there is currently very limited research applying these to abrasion by waterborne solids.

CONCLUSIONS AND RECOMMENDATIONS

This review focused on abrasion of concrete by waterborne solids to understand its mechanisms, evaluate the suitability of existing test methods and investigate the relationship between abrasion loss and compressive strength. The conclusions below can be drawn:

1. Besides modes of abrasive sediment transport, concrete abrasion mechanisms are influenced by the ratio of coarse aggregate to matrix hardness. Concrete mixtures with harder coarse aggregates (CA) relative to the matrix will exhibit plucking of CA and abrasion loss will be a function of its gradation. Conversely, in concrete mixtures with comparative CA and matrix hardness, CA plucking is not an important mechanism in the estimation of abrasion-

erosion loss. There is need for further research to establish threshold conditions for the initiation of CA plucking.

2. The underwater (ASTM C1138) test is the most suitable method for the evaluation of abrasion-erosion resistance of concrete exposed to coarse waterborne solids. This method adequately simulates rolling, sliding and impact wear components of abrasion-erosion and, consequently the important concrete abrasion mechanisms. This is evidenced by the similarities in surfaces of comparable concrete mixtures abraded in the ASTM C1138 test with those observed in spillways and coastal defence elements operating in field conditions. The impact wear is generated by the saltation of steel balls due to surface roughness which occurs once the matrix surface layer has been abraded.

3. Based on the limited pool of test data evaluated, the optimum cube compressive strength for concrete abrasion resistance in the ASTM C1138 test is approximately 60 MPa (8.70 ksi). Therefore, in structures where abrasion resistance governs the concrete grade specification, it would appear that no meaningful improvements in abrasion resistance are achieved by using concrete mixtures with cube compressive strengths exceeding this optimum value.

4. Abrasion-erosion loss in conventional concrete mixtures follows a power function of its compressive strength. A generic abrasion resistance model for concrete has been proposed based on compressive strength. The use of compressive strength for prediction of abrasion resistance is limited by the fact that with compressive strengths of less than 60 MPa (8.70 ksi), the influence of supplementary cementitious materials, coarse aggregate hardness, quantity and gradation becomes prominent. The existing test data is not sufficient to quantify the effects of these parameters on both abrasion-erosion resistance and compressive strength.

5. ASTM C1138 test results and field measurements can be correlated based on the concept of specific energy of the flow. However, this can only be achieved once of the specific energy

of the abrasive in the ASTM C1138 test is quantified hence the need for more research effort to be directed to this area. Further investigations are also required on the influence of concrete: exposure temperature, coarse aggregates (size, shape, texture and quantity), tensile strength and ductility on its abrasion-erosion resistance.

ACKNOWLEDGEMENTS

The work presented here forms part of a wider research project by the authors. The authors wish to express their gratitude and sincere appreciation to the Department of Mechanical, Aerospace and Civil Engineering, University of Manchester for funding this research.

REFERENCES

1. Wentworth, C.K., “A scale of grade and class terms for clastic sediments”. *The Journal of Geology*. 1922; 30(5), pp. 377-392.
2. Allen, R.T.L.; and Terrett, F.L., “Durability of concrete in coast protection works”. *Proceedings of the Coastal Engineering Conference, London, UK*. 1968, paper 97, pp. 1200-1210.
3. Cunningham, L.S.; Farrington, B.; and Doherty, A., “Briefing: Abrasion performance of concrete in coastal structures”. *Proceedings of the Institution of Civil Engineers-Maritime Engineering*. Vol 168(4). 2015, pp. 157-161.
4. ACI Committee 207, “Report on the erosion of concrete in hydraulic structures”. Farmington Hills: American Concrete Institute; 2017.
5. Liu, T.C., “Maintenance and preservation of concrete structures: Report 3-Abrasion-erosion resistance of concrete”. Vicksburg: US Army Corps of Engineers; 1980.
6. McDonald, J.E., “Maintenance and preservation of concrete structures: Report 2-Repair of erosion-damaged structures”. Vicksburg: US Army Corps of Engineers; 1980.
7. Bitter, J.G.A., “A study of erosion phenomena (Part I)”. *Wear*. 1963; 6(1), pp. 5-21.

8. Rabinowicz, E., “Friction and wear of materials”. 2nd ed. Toronto, John Wiley & Sons Inc., 1995
9. Vassou, V.C.; Short, N.R.; and Kettle R.J., “Microstructural investigations into the abrasion resistance of fiber-reinforced concrete floors”. *Journal of Materials in Civil Engineering*. 2008; 20(2), pp. 157-168.
10. Kropp, J.; and Hilsdorf, H.K., “Performance criteria for concrete durability”. 2nd ed London; CRC Press, 1995.
11. Sonebi, M., “Utilization of micro-indentation technique to determine the micromechanical properties of ITZ in cementitious materials”. *Proceedings of ACI session on nanotechnology of concrete: Recent developments and future perspectives*. Denver; 2008, pp. 57-67.
12. Burwell, J.T., “Survey of possible wear mechanisms”. *Wear*. 1957; 1(2), pp. 119-141.
13. Johnson, K.L., “Contact Mechanics”. 1st ed. Cambridge: Cambridge University Press; 1985.
14. Jacobsen, S.; Scherer, G.W.; and Schulson, E.M., “Concrete-ice abrasion mechanics”. *Cement and Concrete Research*. 2015;73, pp. 79-95.
15. Finnie, I., “Erosion of surfaces by solid particles”. *Wear*. 1960; 3(2), pp. 87-103.
16. Lamb, M.P.; Dietrich, W.E.; and Sklar, L.S., “A model for fluvial bedrock incision by impacting suspended and bed load sediment”. *Journal of Geophysical Research: Earth Surface*. 2008; 113(F03025), pp. 1-18.
17. Sklar, L.S.; and Dietrich, W.E., “A mechanistic model for river incision into bedrock by saltating bed load”. *Water Resources Research*. 2004; 40(W06301), pp. 1-22.
18. Ji, T.; Gao, Q.; Zheng, W.; Lin, X.; and Wu, H., “Interfacial transition zone of alkali-activated slag concrete”. *ACI Materials Journal*. 2017; 114(3), pp. 347-354.

19. Liu, T.C., “Abrasion resistance of concrete”. *ACI Journal*. 1981; 78(5), pp. 341-350.
20. ASTM C1138, “Standard test method for abrasion resistance of concrete (Underwater method)”. West Conshohocken: ASTM International; 2012.
21. SL352, “Test code for hydraulic concrete”. Beijing: Chinese Water Conservancy and Electric Power Press (in Chinese); 2006.
22. Kang, J; Zhang, B.; and Li, G., “The abrasion resistance investigation of rubberized concrete”. *Journal Wuhan University of Technology, Materials Science Edition*. 2012; 27(6), pp. 1144-1148.
23. Horszczaruk, E., “The model of abrasive wear of concrete in hydraulic structures”. *Wear*. 2004; 256(7-8), pp. 787-796.
24. ACI Committee 363. “Report on high-strength concrete”. Farmington Hills: American Concrete Institute; 2010.
25. Horszczaruk, E., “Hydro-abrasive erosion of high-performance fiber-reinforced concrete”. *Wear*. 2009; 267(1-4), pp. 110-115.
26. Sonebi, M.; and Khayat, K., “Testing abrasion resistance of high-strength concrete”. *Cement, Concrete and Aggregates*. 2001; 23(1), pp. 34-43.
27. Bagnold, R.A., “An approach to the sediment transport problem from general physics”. *USGS Professional Paper*. 1966, pp. 1-37.
28. Fredsoe, J.; Deigaard, R., “Mechanics of coastal sediment transport”. Vol 3.; World Scientific, 1992.
29. Kryžanowski, A.; Mikoš, M.; Šušteršič, J.; and Planinc, I., “Abrasion resistance of concrete in hydraulic structures”. *ACI Materials Journal*. 2009; 106(4), pp. 349-356.
30. Kryžanowski, A.; Mikoš, M.; Šušteršič, J.; Ukrainczyk, V.; and Planinc, I., “Testing of concrete abrasion resistance in hydraulic structures on the Lower Sava River”. *Strojniški*

- Vestnik/Journal of Mechanical Engineering*. 2012; 58(4), pp. 245-254.
31. Horszczaruk, E., “Mathematical model of abrasive wear of high-performance concrete”.
Wear. 2008; 264(1-2), pp.113-118.
32. Thiruvengadam, A., “The concept of erosion strength”. *Erosion by cavitation or
impingement; ASTM STP 408*, ASTM,1967, pp. 22-34.
33. Engel, P.A., “Impact wear of materials”. 1st ed. New York: Elsevier; 1978.
34. Raphael, J. , “Tensile strength of concrete”. *ACI Journal*. 1984; 81(2), pp. 158-165.
35. Oloukun, F.A., “Prediction of concrete tensile strength from compressive strength:
Evaluation of existing relations for normal weight concrete”. *ACI Materials Journal*.
1991; 88(3), pp. 302-309.
36. Noguchi, T.; Tomosawa, F.; Nemati, K.M.; Chiaia, B.M.; and Fantilli, A.R., “A practical
equation for elastic modulus of concrete”. *ACI Structural Journal*. 2009; 106(5), pp.
690-696.
37. BS EN 1992, “Eurocode 2 - Design of concrete structures. Part 1-1: General rules and
rules for buildings”. London: British Standards Institution; 2008.
38. Liu, T.C.; and McDonald, J.E., “Abrasion-erosion resistance of fiber-reinforced
concrete”. *Cement, Concrete and Aggregates*. 1981; 3(2), pp. 93-100.
39. Sharma, S.; Arora, V.V.; Kumar, S.; Daniel, Y.N.; and Sharma, A., “Durability study of
high-strength steel fiber-reinforced concrete”. *ACI Materials Journal*. 2018; 115(2), pp.
219-225.
40. Berra, M.; Ferrara, G.; and Tavano, S., “Behaviour of high erosion-resistant silica fume-
mortars for repair of hydraulic structures”. *Special Publication*. 1989; 114, pp. 827-847.
41. Abid, S.R.; Hilo, A.N.; and Daek, Y.H., “Experimental tests on the underwater abrasion
of engineered cementitious composites”. *Construction and Building Materials*. 2018;

171, pp. 779-792.

42. Onuaguluchi, O.; and Banthia, N., “Scrap tire steel fiber as a substitute for commercial steel fiber in cement mortar: Engineering properties and cost-benefit analyses”.

Resources, Conservation and Recycling. 2018; 134, pp. 248-256.

43. BS EN 206, “Concrete-Specification , Performance, Production and Conformity”.

London: British Standards Institution; 2016.

44. Neville, A.M., “Properties of Concrete”. 4th ed. Essex: Addison Wesley Longman Limited; 1996.

45. ASTM C779/C779M, “Standard test method for abrasion resistance of horizontal concrete surfaces”. West Conshohocken: ASTM International; 2012.

46. Smoak, G.W.; Husbands, T.B.; and McDonald, J.E., “Repair, evaluation, maintenance and rehabilitation program (Technical Report REMR-CS-52): Results of laboratory tests on materials for thin repair of concrete surfaces”. Vicksburg: US Army Corps of Engineers; 1997.

47. Nazari, A.; and Riahi, S., “Abrasion resistance of concrete containing SiO₂ and Al₂O₃ nanoparticles in different curing media”. *Energy and Buildings*. 2011; 43(10), pp. 2939-2946.

48. Rashwan, M.H.; and Abou-Zeid M.N., “Performance of concrete incorporating stone industry waste as aggregates”. *Transportation Research Record: Journal of the Transportation Research Board*. 2012; 2290(1), pp. 122-129.

49. Horszczaruk, E.; and Brzozowski, P., “Effects of fluidal fly ash on abrasion resistance of underwater repair concrete”. *Wear*. 2017; 376-377, pp.15-21.

50. Horszczaruk, E., “Abrasion resistance of high-strength concrete in hydraulic structures”. *Wear*. 2005; 259(1-6), pp. 62-69.

51. Wang, L.; Yang, H.Q.; Dong, Y.; Chen, E.; and Tang, S.W., “Environmental evaluation, hydration, pore structure, volume deformation and abrasion resistance of low heat Portland (LHP) cement-based materials”. *Journal of Cleaner Production*. 2018; 203, pp. 540-558.
52. Yen, T.; Hsu, T.; Liu Y.; and Chen, S., “Influence of class F fly ash on the abrasion erosion resistance of high-strength concrete”. *Construction and Building Materials*. 2007; 21(2), pp. 458-463.
53. Mohebi, R.; Behfarnia, K.; and Shojaei, M., “Abrasion resistance of alkali-activated slag concrete designed by Taguchi method”. *Construction and Building Materials*. 2015; 98, pp. 792-798.
54. Ramesh, K.G.B; and Sharma, U.K., “Abrasion resistance of concrete containing marginal aggregates”. *Construction and Building Materials*. 2014; 66, pp. 712-722.
55. BS 6349, “Maritime Works – Part 1-4 : General – Code of Practice for Materials”. London: British Standards Institution; 2013.
56. Rogers, J.; Hammer, B.; Brampton, A. et al., “Beach management manual”. 2nd ed. London: CIRIA; 2010.
57. Kiliç, A.; Atiş C.D.; Teymen, A. et al., “The influence of aggregate type on the strength and abrasion resistance of high strength concrete”. *Cement and Concrete Composites*. 2008; 30(4), pp. 290-296.
58. Vander Voort, G.F.; and Lucas, G.M., “Microindentation hardness testing”. *Advanced Materials and Processes*. 1998; 154(3), pp. 21-25.
59. Craig, J.R.; Vaughan, D.J.; and Hagni, R.D., “Ore microscopy and ore petrography”. Vol 406. New York: Wiley; 1981.
60. Young, B.; and Millman, A., “Microhardness and deformation characteristics of ore

- minerals''. *Transactions of the Institution of Mining and Metallurgy*. 1964;(73), pp. 437-466.
61. Xu, J.; and Yao, W., "Nano-scratch as a new tool for assessing the nano-tribological behavior of cement composite". *Materials and Structures*. 2011; 44(9), pp. 1703-1711.
62. Zhao, S.; Van Dam, E.; Lange, D.; and Sun, W., "Abrasion resistance and nanoscratch behavior of an ultra-high performance concrete". *Journal of Materials in Civil Engineering*. 2016; 29(2), pp. 04016212-1-8.
63. Choi, S.; and Bolander, J.E., "A topology measurement method examining hydraulic abrasion of high workability concrete". *KSCE Journal of Civil Engineering*. 2012; 16(5), pp. 771-778.
64. Day, K.W.; Aldred, J.; and Hudson, B., "Concrete mix design, quality control and specification". 4th ed. London: CRC Press; 2014.
65. Bamforth, P., "Enhancing reinforced concrete durability". Surrey: The Concrete Society; 2004.
66. ACI Committee 234. "Guide for the use of silica fume in concrete". Farmington Hills: American Concrete Institute; 2012.
67. Ghafoori, N.; and Diawara, H., "Abrasion resistance of fine aggregate-replaced silica fume concrete". *ACI Materials Journal*. 1999; 96(5), pp. 559-567.
68. Ghafoori, N.; Diawara, H., "Strength and wear resistance of sand-replaced silica fume concrete". *ACI Materials Journal*. 2007; 104(2), pp. 206-214.
69. Laplante, P.; Aitcin, P.; and Vezina, D., "Abrasion resistance of concrete". *Journal of Materials in Civil Engineering*. 1991; 3(1), pp. 19-28.
70. Li, H.; Zhang, M.; and Ou, J., "Abrasion resistance of concrete containing nano-particles for pavement". *Wear*. 2006; 260(11-12), pp. 1262-1266.

71. GB/T 16925, “Test method for abrasion resistance of concrete and its products (Ball bearing method)”. Beijing: Standardization Administration of China Publications; 1997.
72. ASTM C618, “Standard specification for coal fly ash and raw or calcined natural pozzolan for use in concrete”. West Conshohocken: ASTM International; 2015.
73. Osborne, G.J., “Durability of portland blast-furnace slag cement concrete”. *Cement and Concrete Composites*. 1999; 21(1), pp. 11-21.
74. Numata, S.; Koide, Y.; and Shimobayashi, S., “Properties of ultra-highly pulverized granulated blast furnace slag-portland cement blends”. *Special Publication*. 1986; 91, pp. 1341-1360.
75. Fernandez, L.; and Malhotra, V., “Mechanical properties, abrasion resistance, and chloride permeability of concrete incorporating granulated blast-furnace slag”. *Cement, Concrete and Aggregates*. 1990; 12(2), pp. 87-100.
76. Yetgin, S.; and Cavdar, A., “Abrasion resistance of cement mortar with different pozzolanic compositions and matrices”. *Journal of Materials in Civil Engineering*. 2011; 23(2), pp. 138-145.
77. Scrivener, K.L.; Cabiron, J.L.; and Letourneux, R., “High-performance concretes from calcium aluminate cements”. *Cement and Concrete Research*. 1999; 29(8), pp. 1215-1223.
78. Prasittisopin, L.; and Trejo, D., “Characterization of chemical treatment method for rice husk ash cementing materials”. *Special Publication*. 2013; 294, pp. 7.1-7.14.
79. Wada, I.; Kawano, T.; Kawakami, M.; and Maeda, N., “Effect of highly reactive rice husk ash on durability of concrete and mortar”. *Special Publication*. 2000; 192:205-222.
80. Budetta, P.; Galiotta, G.; and Santo, A., “A methodology for the study of the relation between coastal cliff erosion and the mechanical strength of soils and rock masses”.

Engineering Geology. 2000; 56(3-4), pp. 243-256.

81. Dornbusch, U., “The role of water and beach levels in seawall abrasion in the macro-tidal high energy environment of Southeast England”: *Coasts, Marine Structures and Breakwaters: Adapting to Change: Proceedings of the 9th International Conference Organised by the Institution of Civil Engineers*. Edinburgh. 2010, pp. 1-11.

82. ASTM C418, “Standard test method for abrasion resistance of concrete by sand-blasting”. West Conshohocken: ASTM International; 2012.

83. DIN 52108, “Testing of inorganic non-metallic materials-wear test using the grinding wheel according to böhme”.; 2010.

84. Causey, F.E., “Preliminary evaluation of a test method for determining the underwater abrasion- erosion resistance of concrete”. Denver: Bureau of Reclamation, US Department of Interior ; 1985.

85. ASTM C150, “Standard specification for portland cement”. West Conshohocken: ASTM International; 2004.

86. BS EN 197-1. “Composition, specifications and conformity criteria for common cements”. London: British Standards Institution; 2019.

87. ASTM C150, “Specification for portland cement”. West Conshohocken: ASTM International; 1978.

88. ASTM C150, “Standard specification for portland cement”. West Conshohocken: ASTM International; 2000.

89. CAN3-A5-M83, “Portland cements”. Ottawa: Standards Council of Canada; 1983.

90. GB175, “Chinese standard: Common portland cement”. Beijing, China; 2007.

91. IS 8112, “Specifications for 43 grade ordinary portland cement”. New Delhi: Bureau of Indian Standards; 1989.

92. IS 1489, “Part 1: Specifications for portland Pozzolana cement: fly ash-based”. New Delhi: Bureau of Indian Standards; 1991.
93. IS 3812, “Part 1: Pulverished fuel ash-specification for use as pozzolana in cement, cement mortar and concrete”. New Delhi: Bureau of Indian Standards; 2003.
94. IS 12089, “Specification for granulated slag for the manufacture of portland cement”. New Delhi: Bureau of Indian Standards; 1987.
95. IS 15388, “Silica fume – specification”. New Delhi: Bureau of Indian Standards; 2003.
96. IS 12269, “Specification for 53 grade ordinary portland cement”. New Delhi: Bureau of Indian Standards; 2013.

TABLES AND FIGURES

List of Tables:

Table 1 – Abrasion-erosion rates in coastal structures

Table 2 – Test methods for abrasion resistance of concrete

Table 3 – Contradictions in the relation between abrasion loss and compressive strength

List of Figures:

Fig. 1– Concrete revetment-seawall junction abraded in coastal field environment

Fig. 2 – Process of concrete material removal

Fig. 3– Abraded stepped revetment and ASTM C1138 test sample showing similarity

Fig. 4– Variation of concrete abrasion loss with compressive strength

List of Appendices:

Appendix A – Details of concrete mixtures used in the experimental data evaluated

Table 1– Abrasion-erosion rates in coastal structures

Reference	Depth of Wear in mm (in.)	Exposure duration (Years)	Type of structure
Allen and Terret ²	13 to 89 (0.5-3.5)	7	Coastal revetment armour panels
Budetta et al. ⁸⁰	500 (19.7)	18	Seawall
Dornbusch ⁸¹	1500 (59.1)	33	Seawall

Table 2– Test methods for abrasion resistance of concrete

Test method	Test code	Principle of the test	Country
Sand-blasting	ASTM C418 ⁸²	Abrasion resistance of concrete is measured by subjecting samples to action of air-driven silica sand.	United States
Procedure A (Dressing-wheel)	ASTM C779 ⁴⁵	Abrasion is induced on horizontal concrete surface by impact and sliding action of steel dressing-wheels.	United States
Procedure C (Ball-bearings)	ASTM C779 ⁴⁵	Test samples are abraded by high contact stress, impact and sliding friction from ball-bearings.	United States
Bohme	DIN 52108 ⁸³	Concrete cube samples are subjected to wear by a rotating steel grinding disc with an abrasive powder.	Germany
Underwater	ASTM C1138 ²⁰	Concrete resistance is measured by subjecting a disc shaped sample to the action of steel balls transported by agitated water in a steel cylinder.	United States
Ring	SL 352 ²¹	Concrete erosion is measured by abrading sides of a concrete sample annulus with an agitated mixture of sand and water.	China

Table 3– Contradictions in the relation between abrasion loss and compressive strength

Reference	Conclusion
Liu ¹⁹	Resistance increased with increased compressive strength
Horzsczaruk ⁵⁰	
Sonebi and Khayat ²⁶	
Kumar and Sharma ⁵⁴	
Causey ⁸⁴	Resistance has no relation with compressive strength
Kryżanowski ²⁹	Resistance increased with reduced compressive strength
Cunningham et al. ³	Concretes with comparable compressive strengths but differing constituents exhibited varying resistance
Kang et al. ²²	Resistance increased with reduced compressive strength

1

2

1 *Fig. 1–Severe abrasion of a reinforced concrete seawall due to action of wave-driven pebbles*

2
3 *Fig. 2 – Process of concrete material removal*

4
5

Fig. 3 – Abraded coastal revetment armour unit and laboratory sample

Fig. 4– Variation of concrete abrasion loss with compressive strength (MPa=0.145ksi)

Appendix A– Details of concrete mixtures used in the experimental data evaluated

Author Ref.	f _c (MPa)	CA parameters	Binder description	w/b	Test scope
		Key: Rock type (1); MSA (2); Quantity (3); Ratio of CA to FA (4).			Key: Age (1); Curing (2); Compression test specimen (3).
[48]	22.7-52.7	(1)=Basalt, (2)=9.5 and 19 mm (3)=620-685 kg/m ³ , (4)=1.8	375 kg/m ³ OPC Type I ⁸⁵	0.35-0.55	(1)=28 days, (2)=not reported (3)=150 mm cubes
[25]	100.1	(1)=Basalt, (2)=16 mm (3)=1279 kg/m ³ , (4)=1.0	450 kg/m ³ CEM I 52.5R ⁸⁶ 45 kg/m ³ SF	0.30	(1)=28 days, (2)=lime water (3)=150 mm cubes
[50]	89.1-114.4	(1)=Basalt, (2)=8 mm (3)=1006 kg/m ³ , (4)=1.0	470 kg/m ³ CEM I 52.5R, CEM I 42.5R & CEM III/A 42.5N ⁸⁶ 47 kg/m ³ SF	0.26	(1)=28 days, (2)=water (3)=150φ x 300 mm
[19]	28.5-83.0	(1)=Trap rock, (2)= not stated (3)=903-1039kg/m ³ , (4)=1.06-1.14	ASTM Type I ⁸⁷	0.41-0.72	(1)=28 days, (2)=water (3)=150φ x 300 mm
[31]		(1)=Basalt, (2)=16 mm (3)=1153-1279 kg/m ³ , (4)=1.70-2.03	430-520 kg/m ³ CEM I 52.5R ⁸⁶ , 376 kg/m ³ CEM I 32.5R ⁸⁶ 43-52 kg/m ³ SF	0.21-0.5	(1)=28 days, (2)= water (3)=150 mm cubes
[47]	23.6-56.0	(1)=Basalt, (2)=15 mm (3)=1148 kg/m ³ , (4)=2.33	450 kg/m ³ Type I ⁸⁸ ; 0.5-2.0% TiO ₂ and SiO ₂	0.40	(1)=28 days, (2)=lime water (3)=100 mm cubes
[48]	25.9-68.9	(1)=Granite, (2)=9.5 and 19 mm (3)=620-685 kg/m ³ , (4)=1.8	375 kg/m ³ OPC Type I ⁸⁵	0.35-0.55	(1)=28 days, (2)=not reported (3)=150 mm cubes
[51]	30.5-59.7	(1)=Granite, (2)=40 mm (3)=620-685 kg/m ³ , (4)=2.03-2.13	OPC, Low & Moderate heat Portland cements ⁸⁵ .	0.40-0.50	(1)=28, 90 & 180 days, (2)= Fog room, (3)=150 mm cubes
[26]	84.9-112.3	(1)=Granite, (2)=10 mm (3)=940-1090 kg/m ³ , (4)=1.42-1.47	480 kg/m ³ Type 10 & 463-498kg/m ³ Type30 cements ⁸⁹ , 51-55 kg/m ³ SF	0.24	(1)=28 days, (2)=lime water (3)=100φ x 200 mm
[19]	27.3-30.9	(1)=Granite, (2)=not stated (3)=1047-1067 kg/m ³ , (4)=1.43	ASTM Type I ⁸⁷	0.50-0.55	(1)=28 days, (2)=lime water (3)=152φ x 304 mm
[22]	48.8-62.8	(1)=Limestone, (2)=31.5 mm (3)=1213 kg/m ³ , (4)=1.86	400 kg/m ³ OPC P.O 42.5 ⁹⁰ 28 kg/m ³ SF	0.40	(1)=28 days, (2)=water (3)=150 mm cubes
[19]	29.7-81.9	(1)=Limestone, (2)=not stated (3)=893-1013 kg/m ³ , (4)=1.05-1.14	ASTM Type I ⁸⁷	0.41-0.72	(1)=28 days, (2)=lime water (3)= 152φ x 304 mm
[26]	66.9-127.8	(1)=Limestone, (2)=10 mm (3)=930-1100 kg/m ³ , (4) 1.43-1.49	480-490 kg/m ³ Type 10 & 475- 485 kg/m ³ Type 30 cements ⁸⁹ , 52-54 kg/m ³ SF	0.24	(1)=28 days, (2)=lime water (3)=100φ x 200 mm
[48]	23.3-58.6	(1)=Dolomite, (2)=9.5 and 19 mm (3)=1081-1201 kg/m ³ , (4)=1.77	375 kg/m ³ OPC Type I ⁸⁵	0.35-0.55	(1)=28 days, (2)=Not reported (3)=150 mm cubes
[49]	45.9-62.2	(1)=Natural gravel, (2)=16 mm (3)=1028 kg/m ³ , (4)=1.73	450 kg/m ³ CEM I 42.5R ⁸⁶ Fly ash in percentages of 0, 20, 30, 40 and 50%.	0.40	(1)=28 & 58 days, (2)=water (3)=100 mm cubes
[3]	62.1-62.6	(1)=Gravel, (2)=20 mm (3)= 910 kg/m ³ , (4)= 1.63	275 Kg/m ³ CEM III ⁸⁶ 155 kg/m ³ ggbs	0.38-0.39	(1)=128 & 129 days, (2)=water (3)=150 mm cubes
[54]	30.2-69.3	(1)=Marginal rock, (2)= 31.5 mm (3) =989-1270 kg/m ³ , (4)=1.62-2.07	315-554 kg/m ³ OPC 43 ⁹¹ & PPC ⁹² , 40% Fly ash ⁹³ ; 15 & 40% ggbs ⁹⁴ ; 10% SF ⁹⁵	0.28-0.63	(1)=28 & 90 days, (2)=water (3)=150 mm cubes
[52]	35.9-118.1	(1)=Crushed stone, (2)=19 mm (3)=743-1008 kg/m ³ , (4)=0.79-2.23	275-643 kg/m ³ Type I ⁸⁵ cement; 0, 15, 20, 25 & 30% Class F Fly ash ⁷²	0.28-0.54	(1)=28, 91 & 182 days, (2)=air (3)=100φ x 200 mm
[39]	88.3	(1)=Crushed stone, (2)=20 mm (3)=1116kg/m ³ , (4)=1.64	548 kg/m ³ OPC 53 ⁹⁶ 61 kg/m ³ SF	0.23	(1)=28 days, (2)=water [†] (3)=150 mm cubes [†]
[53]	32.3-55.6	(1)=Crushed stone, (2)=12 mm (3)=924 kg/m ³ (4)=1.00	368-394 kg/m ³ ggbs; 79-153 kg/m ³ NaOH; 26-92 kg/m ³ Na ₂ SiO ₂	0.40-0.50	(1)=28 days (2)=air at 23-25°C [†] (3) 100 mm cubes
Key: CA = course aggregates, FA = fine aggregates, f _c = compressive strength, GGBS = ground granulated blast furnace slag, MSA = Maximum size of aggregate, OPC = ordinary Portland cement, PPC = Portland Pozzolana cement, SF = silica fume, w/b = water to binder ratio. †=Others cured in oven at 60-95°C for 24 hours and then in curing room until expiry of 28 days. ‡=Not stated, hence assumed. Conversions: 1 mm= 0.0394 inches; 1 kg/m ³ =1.6856 lb/yd ³ and 1 MPa=0.145 ksi.					